

CHAPTER 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
TABLE OF CONTENTS

Section	Title	Page
22.1	Right-of-Way Grading	22-1
22.1.1	Site Remediation	22-1
	A. Disposal of Waste Materials	22-1
22.1.2	Site Demolition	22-1
	A. Removal of structures and Obstructions	22-1
22.1.3	Site Clearing and Grubbing	22-2
	A. General	22-2
	B. Construction Requirements	22-2
22.1.4	Embankment and Excavation	22-3
	A. General Construction Requirements	22-3
	B. Embankment Material	22-3
	C. Excavation	22-3
22.1.5	Embankment Construction	22-4
	A. General	22-4
22.1.6	Borrow Material	22-5
	A. General	22-5
	B. Satisfactory Borrow Materials	22-5
	C. Unsatisfactory Borrow Materials	22-5
22.1.7	Earthwork Grading	22-5
	A. General	22-5
	B. Grading During Construction	22-522-522-6
	C. Accessibility During Construction	22-6
	D. Site Grading	22-6
22.1.8	Erosion Control	22-6
	A. Soil Protection	22-6
	B. Fort Collins (City Limits Only)	22-6
	C. Larimer County GMA	22-622-622-7
	D. Loveland (City Limits Only)	22-7
22.2	Trenching for Utilities	22-722-722-16
22.2.1	Excavation for Utility Trenches	22-722-722-16
	A. General	22-722-722-16
	B. Tracked Vehicles	22-722-722-16
	C. Removal of Pavement	22-722-722-16
	D. Protection of Existing Underground Utilities	22-722-722-16
	E. Relocation of Utilities	22-722-722-16
	F. Subdrains	22-722-722-16
	G. Trenching Through Existing Pavement	22-722-722-16
22.2.2	Utility Crossings	22-822-822-17
	A. Trenches	22-822-822-17
	B. Markings on Concrete Patches	22-822-822-17
22.2.3	Backfill	22-822-822-17
	A. Ordinary/Native Backfill	22-822-822-17
	B. Imported Backfill	22-822-822-17
	C. Structure Backfill	22-822-822-17
	D. Flowable Fill	22-822-822-17
	E. Conventional Backfill	22-922-922-18
22.2.4	Trench Cover	22-922-922-18
	A. Subgrade	22-922-922-18
22.3	Structures	22-1022-1022-19

22.3.1	General	22-1022-1022-19
22.3.2	Removal of Structures	22-1022-1022-19
22.3.3	Excavation for Structures	22-1022-1022-19
	A. Tolerance and Placement	22-1022-1022-19
	B. Excavations for Footings and Foundations.....	22-1022-1022-19
	C. Excavation for Underground Structures.....	22-1022-1022-19
22.3.4	Structure Backfill Material	22-1022-1022-19
22.3.5	Markings	22-1022-1022-20
22.3.6	Materials	22-1122-1122-20
	A. Concrete	22-1122-1122-20
	B. Structural Steel.....	22-1122-1122-20
	C. Steel Structural Plate	22-1222-1222-21
	D. Timber	22-1222-1222-21
	E. Bearing Device	22-1222-1222-21
	F. Pipe Railing.....	22-1222-1222-21
	G. Concrete Reinforcement.....	22-1222-1222-21
22.3.7	Construction Requirements	22-1522-1522-24
	A. Structural Concrete.....	22-1522-1522-24
	B. Structural Steel.....	22-1922-1922-28
	C. Structural Plate.....	22-1922-1922-29
	D. Timber	22-2022-2022-29
	E. Bearing Device	22-2022-2022-29
	F. Pipe Railing.....	22-2022-2022-29
	G. Cold Weather Requirements.....	22-2022-2022-29
22.4	Non-Structural Concrete	22-2022-2022-30
22.4.1	General	22-2122-2122-30
	A. Protection	22-2122-2122-30
	B. Damaged Concrete	22-2122-2122-30
	C. Sequence of Construction	22-2122-2122-30
22.4.2	Materials and Methods	22-2122-2122-31
	A. Concrete	22-2122-2122-31
	B. Job-Mixed Concrete	22-2222-2222-32
	C. Ready-Mixed Concrete.....	22-2322-2322-32
22.4.3	Construction	22-2322-2322-32
	A. Concrete Finishing.....	22-2322-2322-32
	B. Repairs.....	22-2422-2422-33
	C. Concrete Curing	22-2422-2422-33
	D. Cold Weather Requirements	22-2422-2422-34
	E. Joints.....	22-2522-2522-34
	F. Backfilling.....	22-2522-2522-34
	G. Opening to Traffic	22-2522-2522-35
	H. Warranty.....	22-2522-2522-35
	I. Initial and Final Acceptance	22-2522-2522-35
22.4.4	Tunneling or Boring Under Curb, Gutter, Walks, and Pavements	22-2622-2622-35
	A. General	22-2622-2622-35
	B. Borings	22-2622-2622-35
22.5	Pavement	22-2622-2622-36
22.5.1	General	22-2622-2622-36
22.5.2	Fill	22-2622-2622-36
	A. Engineered Fill.....	22-2622-2622-36
22.5.3	Subgrade and Roadbed	22-2722-2722-36
	A. General	22-2722-2722-36
	B. Subgrade Approval	22-2722-2722-36
	C. Subgrade Preparation.....	22-2722-2722-36

	D. Subgrade Protection.....	22-2822-2822-37
	E. Soil Stabilization.....	22-2822-2822-37
	F. Subgrade Surface Tolerance.....	22-3222-3222-42
22.5.4	Subbase.....	22-3222-3222-42
	A. Materials.....	22-3222-3222-42
	B. Application.....	22-3322-3322-42
	C. Surface Tolerance.....	22-3322-3322-42
22.5.5	Base Course.....	22-3322-3322-42
	A. General.....	22-3322-3322-43
	B. Aggregate Base Course Material.....	22-3322-3322-43
	C. Cement Treated Aggregate Base Course Material.....	22-3422-3422-43
	D. Application.....	22-3422-3422-44
	E. Surface Tolerance.....	22-3422-3422-44
	F. Soil Sterilization.....	22-3422-3422-44
22.5.6	Portland Cement Concrete Pavement.....	22-3522-3522-44
	A. Materials.....	22-3522-3522-44
	B. Concrete Forms.....	22-3622-3622-45
	C. Construction.....	22-3622-3622-46
	D. Warranty.....	22-3822-3722-47
	E. Initial and Final Acceptance.....	22-3822-3722-47
22.5.7	Hot Bituminous Asphalt Pavement – Superpave Method.....	22-3822-3722-47
	A. Materials.....	22-3822-3822-47
	B. Superpave Job Mix.....	22-4622-4622-55
22.5.8	Construction Requirements.....	22-4922-4922-58
22.6	Miscellaneous.....	22-5022-5022-59
22.6.1	Rebuilt Miscellaneous Structures.....	22-5022-5022-59
	A. General.....	22-5022-5022-59
	B. Construction.....	22-5022-5022-59
22.6.2	Traffic Signals, Signing, and Striping.....	22-5122-5122-59
	A. General.....	22-5122-5122-59
	B. Traffic Signal.....	22-5122-5122-60
	C. Traffic Signal Controller.....	22-5122-5122-60
	D. Traffic Signing.....	22-5222-5222-60
	E. Traffic Striping and Marking.....	22-5322-5322-62
22.6.3	Bus Shelters.....	22-5522-5522-64
22.6.4	Streetscape Standards - Fort Collins (City Limits Only).....	22-5622-5622-64

LIST OF TABLES

Table 22-1 Required Density for Stabilized Compaction.....	22-3122-3122-40
Table 22-2 Fine Aggregates for Portland Cement Concrete	22-3622-3522-45
Table 22-3 Coarse Aggregates for Portland Cement Concrete	22-3622-3622-45
Table 22-4 (CDOT 703-3) Master Range Table for Hot Bituminous Pavement	22-3822-3822-47
Table 22-5 Clay Content Criteria	22-3922-3922-48
Table 22-6 Criteria for Thin, Elongated Particles.....	22-3922-3922-49
Table 22-7 Design Mix Criteria	22-4122-4122-51
Table 22-8 Laboratory Mix Design Temperatures.....	22-4322-4322-52
Table 22-9 Minimum Voids in the Mineral Aggregate (VMA).....	22-4322-4322-52
Table 22-10 Asphalt Cements Permitted	22-4422-4422-53
Table 22-11 Binder Grade Requirement.....	22-4422-4422-53
Table 22-12 Grade Bumping Criteria	22-4522-4522-54
Table 22-13 Grade Reduction for Lower Lifts.....	22-4522-4522-54
Table 22-14 Tolerances for Hot Mix Asphalt	22-4922-4922-57
Table 22-15 Placement Temperature Limitations in °C	22-4922-4922-58

LIST OF FIGURES

This Chapter Contains No Figures

CHAPTER 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS

22.1 RIGHT-OF-WAY GRADING

22.1.1 Site Remediation

A. Disposal of Waste Materials

1. Burning on Developer's Property. Burning is not permitted on Developer's property except for training burns authorized and overseen by the local fire authority.
2. Removal from Developer's Property. Removal of waste materials and unsuitable or excess topsoil from the Developer's property shall be legally disposed of.

22.1.2 Site Demolition

A. Removal of structures and Obstructions

1. General. The work shall consist of removal, salvaging, and backfilling according to **CDOT Specifications Section 202.01**. Refer also to **Ch. 25, Reconstruction and Repair**.
 - a. Salvage. Salvageable material shall be handled according to **CDOT Specifications Section 202.03** in locations designated by the Local Entity Engineer.
 - b. Disposal.
 - 1) Developer Responsibility. The Developer shall make all necessary arrangements for securing legal and suitable disposal sites.
 - 2) Unestablished Dump Sites. If disposal is to be at other than established dump sites, the Local Entity Engineer may require the Developer to furnish written permission from the property owner on whose property the materials are placed.
 - 3) Concrete and Asphalt. Broken concrete and asphalt, with no other waste material, may be taken to Local Entity's recycling yard. Asphalt and concrete must be separated. Mingling of materials is prohibited.
 - c. Backfill. Except in areas to be excavated, all cavities left by structure removal shall be cut to clean undisturbed material and backfilled with suitable material and compacted in accordance with Section 22.2.3 of these Standards. Jetting or ponding will not be allowed.
 - d. Preservation of Property. Existing improvements, adjacent property, utilities, trees, and plants that are not to be removed shall be protected from injury or damage resulting from the Developer's operations.
 2. Construction Requirements.

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.1 Right-of-Way Grading

- a. Structures. The Developer shall raze, remove, and dispose of all structures, according to **CDOT Specifications Section 202.02**.
- b. Demolition Permit. Building demolition requires a demolition permit issued by the Local Entity.
- c. Abandoned pipelines/conduits. Abandoned pipelines and conduits shall be removed or abandoned in place by plugging and filling with sand or appropriate alternative in accordance with direction from the Local Entity Engineer.
- d. Other Obstructions.
 - 1) Miscellaneous Obstructions. The Developer shall remove miscellaneous obstructions and properly dispose of them.
 - 2) Traffic Signals and Signs. Removal of traffic signals and related materials shall be per **CDOT Specifications Section 202.02**. All traffic signal equipment shall remain the property of the Local Entity. Contact the Local Entity Engineer for disposal instructions.
 - 3) Portions of Structures. Removal of portions of structures shall be per **Section 22.3.2** of these standards.
 - 4) Detour Structures. Materials used in detour structures for the project shall be removed according to **CDOT Specifications Section 202.06**.

22.1.3 Site Clearing and Grubbing

A. General

The work shall consist of clearing, grubbing, removing, and disposing according to **CDOT Specifications Section 201.01**. This work does not include objects designated to remain nor which are to be removed in accordance with other sections of these Standards.

B. Construction Requirements

Construction requirements for site clearing and grubbing shall follow those requirements outlined in **CDOT Specifications Section 201.02** with the addition of the following:

1. Construction Limits. The Developer will establish construction limits in accordance with the Local Entity requirements.
2. Buried Perishable Objects. Buried perishable objects shall be removed to a depth of 3 feet below the existing ground or subgrade, whichever is lower.
3. Burning. Burning of perishable material shall be done in accordance with in **Section 22.1.1 A**.
4. Disposal. Disposal of materials or debris shall be done in accordance with **Section 22.1.1 A**.

22.1.4 Embankment and Excavation

A. General Construction Requirements

Excavation and embankment operations shall be done in accordance with **CDOT Specifications Section 203.04**. Prior to beginning grading operations in any area, all necessary clearing and grubbing in that area shall have been performed in accordance with **Section 22.1.3**.

B. Embankment Material

Embankment material shall consist of approved material acquired from excavations, and shall be hauled and placed in embankments in reasonably close conformity with the line, grades, thicknesses, and typical cross-sections shown on the plans.

1. Compaction. The embankment shall be free of organic material, and shall be moisture treated to within 2% (or as specified on the plans or geotechnical report) of optimum moisture content and placed in 6-inch lifts compacted to 95% standard proctor.
2. Source of Material. When the source of embankment materials is not designated on the plans, approval of the source will be contingent on the material meeting the requirements of **Chapter 5, Soils Investigations**, and having a resistance value that matches or exceeds the R-value of the in-situ material or as shown on the plans when tested by the Hveem Stabilometer.
3. Unsatisfactory Material. Refer to the unacceptable soil classification groups from **ASTM** which apply for locally available material. No top soil shall be used for fill. In addition, no gap graded material nor material weighing less than 90 pounds per cubic foot shall be used for fill.

C. Excavation

1. General. This work shall consist of excavation, disposal, shaping, or compaction of all material encountered within the limits of the work, including excavation for ditches and channels.
 - a. Protection of Property and Workmen. Excavation shall be performed in a careful and orderly manner with due consideration given to protection of adjoining property, the public, and workmen.
 - b. Damage Repair Responsibility. Any damage to streets, parking lots, utilities, irrigation systems, plants, trees, building or structures or private property, or the bench marks and construction staking shall be repaired and restored to its original conditions by the Developer at the Developer's expense. Following completion of construction, should any of these trees, shrubs, or irrigation facilities, etc. require replacement, it shall be done at the Developer's expense.
 - c. Compliance with Standards. All excavation and the like shall comply with OSHA's "Construction Industry Standards" as well as all applicable Federal and State regulations.
 2. Stockpile. Refer to Chapter 25, Reconstruction and Repair.

3. Disposal. Excess excavated material shall be disposed of outside of the Right-of-Way unless approval is given by the Local Entity Engineer to do otherwise.
4. Explosives. The use of explosives will not be permitted without a blasting permit issued by the local fire authority. Refer to **Chapter 6, Permits**, for permit conditions and procedures.
5. Unsanitary Materials. Unacceptable material defined as any earthen material containing vegetable or organic silt, topsoil, frozen material, trees, stumps, certain manmade deposits, or industrial waste, sludge, or landfill, or other undesirable materials will be removed from the site and disposed of in accordance with applicable Local Entity, State, and Federal requirements.
6. Unauthorized Excavation. Unauthorized excavation consists of removal of materials beyond specified elevations without the specific direction of the Local Entity Engineer. Unauthorized excavation shall be backfilled and compacted as specified for authorized excavations.
7. Rock. Rock shall be excavated and disposed of according to **CDOT Specifications Section 203.05(a)**, or Local Entity Requirements. Rock shall be removed to a level 3 feet below the subgrade surface within the right-of-way. Drainage facilities may be required by the Local Entity Engineer.
8. Excavation for Appurtenances. See Section 22.4.4 .

22.1.5 Embankment Construction

A. General

Embankment construction shall consist of constructing roadway embankments within project areas where unsuitable material has been removed as well as in other areas as noted in **CDOT Specifications Section 203.06**.

1. Water in Material. Free running water shall be drained from the material before the material is placed.
2. Maximum Size of Solid Material. Rocks, broken concrete, or other solid materials more than 3 inches in greatest dimension shall not be placed in embankment, unless approved by Local Entity Engineer.
3. Archaeological Sites or Artifacts. When the Developer's excavating operations encounter remains of prehistoric peoples' dwelling sites or artifacts of historical or archaeological significance, the operations shall be temporarily discontinued. The Developer shall contact archaeological authorities to determine the disposition thereof. When directed, the Developer shall excavate the site in such manner as to preserve the artifacts encountered and shall remove them for delivery to the custody of the proper state or Local Entity authorities.
4. Protection of Existing Installations. The Developer shall at all times take precautions for the protection of culverts, irrigation crossings, mail boxes, driveway approaches, valve boxes, manholes, survey monuments, underground or

overhead utility lines, and all other public or private installations that may be encountered during construction. The Developer shall be responsible for the repair of any installations damaged due to their work. Manholes and valve boxes shall be observed by the Local Entity Engineer for displacements and introduction of foreign matter. It shall be the Developer's responsibility to correct any displacement and to remove any foreign matter resulting from the Developer's work.

22.1.6 Borrow Material

A. General

Provide approved borrow soil materials from off-site locations when sufficient approved soil materials are not available from excavations on-site. Borrow material shall be placed only after the approved excavation material has been replaced in the fill. Borrow areas shall be finished so that water will not collect or stand therein. The "R" value of the borrow shall be equal or greater than the design "R" value required for the existing subgrade soil. In addition, the LL and PI shall be equal to, or better than, the LL and PI of the subgrade material. Refer to **Chapter 10, Pavement Design and Technical Criteria**.

B. Satisfactory Borrow Materials

Borrow material must be free of rock or gravel larger than 3 inches, and free of debris, waste, frozen materials, vegetation and other deleterious matter. Refer to **ASTM** soil classification groups which apply for locally available material.

C. Unsatisfactory Borrow Materials

Refer to the unacceptable soil classification groups from **ASTM** which apply for locally available material. No top soil shall be used for fill. In addition, no gap graded material nor material weighing less than 90 pounds per cubic foot shall be used for fill.

22.1.7 Earthwork Grading

A. General

Grade all areas to a uniformly smooth surface, free from irregular surface changes. Comply with compaction requirements and grade to cross-sections, lines, and elevations indicated. Provide a smooth transition between existing adjacent grades and new grades.

Remove soft spots, fill low spots, and trim high spots to conform to required surface tolerances.

B. Grading During Construction

Grading shall be done as necessary to prevent surface water from entering the excavation. Any other water accumulation therein shall be promptly removed.

C. Accessibility During Construction

Earthwork construction shall be performed in a manner that does not obstruct surface drainage or prohibit access to operational driveways, fire hydrants, manholes, and water valves.

D. Site Grading

1. Slope and Elevation of Grades. The ROW shall be sloped to direct storm runoff flow to the roadway, unless otherwise specified on the plans. Finish subgrades to required elevations within the following tolerances:

- a. Lawn or Unpaved Areas. Plus or minus 0.25feet.
 - b. Walks. Plus 0 or minus 0.1 feet.
 - c. Pavements. Plus 0 or minus .04 feet.
2. Construction Stakes. The Developer shall provide all stakes necessary for curb, gutters, sidewalks and structures and furnish all necessary information relating to lines and grades. The Developer shall be held responsible for preservation of all such stakes.
- a. Stake Removal The Developer shall not remove stakes until three working days after placement of concrete unless approved by the Local Entity Engineer.
 - b. Vertical Curves. Curb stakes shall be placed at 25 foot intervals and at the lowest and highest elevations along the vertical curve. This is intended to minimize flat grades at the high and low points.

22.1.8 Erosion Control

A. Soil Protection

All disturbed soil, on or off-site and related to work at the project site, is required to be protected from wind and storm water erosion. To mitigate erosion, the contractor shall use standard erosion control techniques described in “Volume 3 – Best Management Practices of the Urban Storm Drainage Criteria Manual,” published by the Urban Drainage and Flood Control District.

B. Fort Collins (City Limits Only)

Erosion control standards for Fort Collins (city limits only) shall follow the **City of Fort Collins Storm Water Utility Specifications.**

C. Larimer County GMA

Erosion control standards are found in Larimer County Storm Water Management Manual, Section 10.

D. Loveland (City Limits Only)

Erosion control standards for Loveland (city limits only) shall follow the **City of Loveland Storm Drainage Standards**.

22.2 TRENCHING FOR UTILITIES

22.2.1 Excavation for Utility Trenches

A. General

All trenching activities shall comply with the requirements of OSHA's "Construction Industry Standards" as well as all applicable Federal and State regulations for safety.

Trenches shall be excavated, shored or graded, with sides sloped to conform to the requirements for the soil conditions.

No more than 300 feet of trench length shall be open at any time, unless approved by the Local Entity Engineer.

Repair of failed trenches, and all associated pavement patching and concrete repairs will be the responsibility of the party requiring the trench, and shall be repaired in accordance with Chapter 25. The Local Entity may require mill and inlay or overlay of the affected areas.

B. Tracked Vehicles

No tracked vehicles shall be permitted on streets unless approved by the Local Entity Engineer. When tracked vehicles are allowed, existing facilities will be restored to original condition at the Developer's expense.

C. Removal of Pavement

Refer to Chapter 25, Reconstruction and Repair.

D. Protection of Existing Underground Utilities

Refer to Chapter 25, Reconstruction and Repair.

E. Relocation of Utilities

Refer to Chapter 25, Reconstruction and Repair.

F. Subdrains

Subdrains shall only be installed where shown on, and in accordance with, the approved plans.

G. Trenching Through Existing Pavement

Refer to Chapter 25, Reconstruction and Repair.

22.2.2 Utility Crossings

A. Trenches

All utility trenches that must be in existing streets shall be backfilled with flowable fill after the utility line has been installed, unless otherwise directed by the Local Entity Engineer. Refer to **Section 22.2.3** for flow fill criteria.

B. Markings on Concrete Patches

Refer to the discussion on markings in **Section 22.4.3 A** about concrete finishing.

22.2.3 Backfill

A. Ordinary/Native Backfill

This shall consist of material excavated from the site except rubbish, frozen material, broken pavement, stones, or other consolidated material greater than 3 inches in diameter, organic muck, or other materials considered unacceptable by the Inspector.

B. Imported Backfill

See Section 22.1.6 Borrow Material.

C. Structure Backfill.

This material shall be Class I structure backfill, conforming to **CDOT Standard Specifications, Section 703**. Class I structure backfill shall be used on all bridges, box culverts, or where otherwise specified.

D. Flowable Fill

This material shall be required as utility trench backfill unless otherwise directed by the Local Entity Engineer. This requirement applies to all locations under existing pavement. Vibration of flowable fill shall be required unless otherwise approved by the Local Entity Engineer. The approved mix for flowable fill is shown below:

Flowable Fill Ingredients	Pounds/Cubic Yard
Cement*	42 (0.45 sack)
Water	325 (39 gallons as needed)
Coarse Aggregate (No.57)	1700
Sand (ASTM C-33)	1845

*fly ash may be approved by the Local Entity Engineer. Curing accelerators (“flash-fill”) shall not be used

The maximum desired 28-day strength is 60 psi. The combination of material listed above, or an equivalent, may be used to obtain the desired flowable fill. Flowable fill shall not be used as a temporary or permanent street surface.

Trenches shall be initially backfilled to the level of the original surface. After flowable fill has cured, the top surface of the flowable fill shall be removed to the depth necessary to allow repair of the permanent surface.

E. Conventional Backfill

Conventional backfill is “nonflowable fill.”

1. Backfill Lifts. Backfill material shall be placed in uniform loose lifts, not to exceed 8 inches prior to compaction. Alternate methods may be considered by the Local Entity Engineer.
2. Compaction. Each layer shall be compacted to a density not less than 95 percent of maximum density, in accordance with **AASHTO T99** and at the moisture content as specified in the soils or pavement design report. If the moisture content is not specified, soils shall be compacted at +/- 2 percent.
3. Categories of Conventional Backfill. Backfill lifts under existing or proposed streets, curbs, gutters, sidewalks, and alleys is divided into 3 categories: initial, intermediate, and final lifts as defined below.
 - a. Initial Lift (bedding). This is designated as Class B and generally comprised of a washed, clean gravel material, consisting of the section from the bottom of the excavation to a point 12 inches above the top of the underground structure installation. Placement and compaction of the initial layer shall be as specified by the utility to protect their installation. Sections deeper than described above for class B will not be allowed.
 - b. Intermediate Lift. This is generally comprised of native material, consisting of the section above the initial layer to a point within 6 inches of the ground level or the bottom of the pavement section, whichever is greater. Excavated material maybe used in the intermediate layer provided that it is deemed suitable by the Local Entity Engineer.
 - c. Final Lift. This includes both roadbase and surfacing material. Roadbase material shall be CDOT class 5 or 6 aggregate course as specified in the pavement design report or as specified by the Local Entity Engineer.

22.2.4 Trench Cover

A. Subgrade

1. Compaction. After the backfill has been placed and compacted as specified, it shall be cut and trimmed to the required depth and cross section (see Section 25.5 Pavement). Trench cover subgrade shall be free of all rock over 3 inches in size. It shall be compacted to not less than the densities required for the given soil classification as listed in **Section 22.5.2 C22.5.3-C**. This density requirement also applies to all utility trenches within the public Right-of-Ways. Compaction shall be evaluated by standard tests, (see **Table 23-1**), at the time of constructing curb, gutter, sidewalk, pavement, and/or other permanent trench cover structure.
2. Excess Excavated Material. All excess excavated material shall be removed and disposed of outside the legal limits of the Right-of-Way as the work progresses,

unless the approval of the Local Entity Engineer is obtained for disposal of the material within the legal limits of the Right-of-Way.

3. Condition Restored. All parts of the roadway and various structures disturbed shall be restored in accordance with these Standards.
4. Compaction Equipment. Compaction equipment must be on the job site before excavation is started. Compaction equipment must be capable of compacting within the trench width limits to avoid bridging the ditch.

22.3 STRUCTURES

22.3.1 General

This section discusses the removal, excavation, and backfill for structures as well as specifications for materials and construction criteria.

22.3.2 Removal of Structures

Refer to **Chapter 25, Reconstruction and Repair**.

22.3.3 Excavation for Structures

A. Tolerance and Placement

Excavations shall be done in accordance with the designed elevations and dimensions within a tolerance of plus or minus 1.2 inches. Excavations shall be extended a sufficient distance from structures for placing and removing concrete form work, installing services, and other construction, and for inspections.

B. Excavations for Footings and Foundations

Do not disturb bottom of excavation. Excavate by hand, if needed, to final grade just before placing concrete reinforcement. Trim bottoms to required lines and grades to leave solid base for receiving other work.

C. Excavation for Underground Structures

Excavation for tanks, basins, and mechanical or electrical appurtenances shall be to elevations and dimensions indicated within a tolerance of plus or minus 1.2 inches. The bottom of excavations intended for bearing surface shall not be disturbed.

22.3.4 Structure Backfill Material

Refer to **Section 22.2.3** for backfill to be used for structures.

22.3.5 Markings

All bridges, retaining walls, and box culverts shall have the year of construction permanently impressed therein. The impression for bridges and box culverts shall be

located on the downstream head wall face in legible numbers as per **Section 22.4.3 A**. The Local Entity shall determine the location of the indented construction year for all retaining walls and the size of letters shall be per **Section 22.4.3 A**.

22.3.6 Materials

A. Concrete

1. Aggregate. Refer to Section 22.4.2 A.
2. Waterproofing Membrane. An approved waterproofing membrane shall be furnished according to these specifications. Refer to **CDOT Specifications Sections 515.01 and 515.02**.
3. Waterstops. Appropriate size and type of waterstop shall be furnished in accordance with these specifications and in conformance with the plans. Refer to **CDOT Specifications Section 518.02**.

B. Structural Steel

1. Structural Carbon Steel. Structural Carbon steel shall be furnished in accordance to these specifications and in conformance with the plans. Refer to **CDOT Specifications Section 509.03**.
2. High-Strength Low-Alloy Structural Steel. High-strength low-alloy structural steel shall be furnished in accordance to these specifications. Refer to **CDOT Specifications Section 509.04**.
3. Self Weathering Tubing. Self weathering tubing shall be furnished according to **CDOT Specifications Section 509.05**.
4. Structural Tubing. Structural tubing shall be furnished in accordance with **CDOT Specifications Section 509.06**.
5. Bolts. Bolts shall be furnished in accordance to **CDOT Specifications Section 509.07**.
6. High Strength Bolts. High strength bolts shall be furnished in accordance with **CDOT Specifications Section 509.08**.
7. Pins and Rollers. Pins and rollers shall be furnished in accordance with **CDOT Specifications Section 509.09**.
8. Anchor Bolts. Anchor bolts shall be furnished in accordance with **CDOT Specifications Section 509.10**.
9. Galvanized and Metallized Steel. Galvanized and metallized steel shall be furnished in accordance with **CDOT Specifications Section 509.11**.
10. Welded Stud Shear Connectors. Welded stud shear connectors are to be furnished in accordance with **CDOT Specifications Section 509.12**.

C. Steel Structural Plate

Steel plate structures shall consist of materials as specified on the plans and be in accordance with **CDOT Specifications Section 510.02**.

D. Timber

1. General Timber. Timber shall be furnished in accordance with **CDOT Specifications Section 508.02**.
2. Treated Timber. Treated timber shall be furnished in accordance with **CDOT Specifications Section 508.03**.
3. Hardware. Hardware for timber construction shall be furnished in accordance with **CDOT Specifications Section 508.05**.

E. Bearing Device

Bearing device materials shall be furnished in accordance with **CDOT Specifications Section 512.02**.

F. Pipe Railing

Pipe for railing shall conform to the plans and be furnished in accordance with **CDOT Specifications Section 514.02**.

G. Concrete Reinforcement

1. Reinforcing Materials – General.

- a. Reinforcing Bars. ASTM A 615 Grade 60, deformed (unless otherwise specified on plans).
- b. Supports for Steel Reinforcement. Bolsters, chairs, spacers, and other devices for spacing, supporting, and fastening reinforcing bars and welded wire fabric in place. Use wire bar-type supports complying with CRSI specifications.
 - 1) For slabs-on-grade, use supports with sand plates or horizontal runners where base material will not support chair legs.
 - 2) For exposed-to-view concrete surfaces where legs of supports are in contact with forms, provide supports with legs that are protected by plastic (CRSI, Class 1) or stainless steel (CRSI, Class 2).
2. Shop Drawings.
 - a. Drawings. Before fabrication of the reinforcement, the Developer shall prepare or have prepared complete bending, fabrication, and setting drawings and bar lists covering all required reinforcement steel.
 - b. Review. Drawings and bar lists shall be submitted to the Local Entity Engineer for review of general conformity to specified requirements. The review of the Shop Drawings by the Local Entity Engineer in no way relieves the Developer of sole responsibility for correct placement of reinforcing steel.

3. Placing Reinforcement.

- a. General. Comply with Concrete Reinforcing Steel Institute’s recommended practice for “Placing Reinforcing Bars,” for details and methods of reinforcement placement and supports, and as specified.
- b. Vapor Retarder/Barrier. Avoiding cutting or puncturing vapor retarder/barrier during reinforcement placement and concreting operations. Repair damages before placing concrete.
- c. Cleaning. Clean reinforcement of loose rust and mill scale, earth, ice, and other materials that reduce or destroy bond with concrete.
- d. Positioning to Prevent Displacement. Accurately position, support, and secure reinforcement against displacement. Locate and support reinforcing by metal chairs, runners, bolsters, spacers, and hangers, as approved by the Local Entity Engineer.
- e. Tie Bars, Bar Supports, and Wire Ties. Place reinforcement to maintain minimum coverages as indicated for concrete protection. Arrange, space, and securely tie bars and bar supports to hold reinforcement in position during concrete placement operations. Set wire ties so ends are directed into concrete, not toward exposed concrete surfaces.
- f. Wire Fabric. Install welded wire fabric in lengths as long as practicable. Lap adjoining pieces at least one full mesh and lace splices with wire. Offset laps of adjoining widths to prevent continuous laps in either direction.
- g. Bending and Placing. Reinforcing steel, before being placed, shall be thoroughly cleaned of coatings that will destroy or reduce bond. A light coating of rust may be allowed by the Local Entity Engineer. Reinforcement shall be carefully formed to the dimensions indicated on the plans. It shall not be bent or straightened in a manner that will injure the material. THE USE OF HEAT IN BENDING BARS SHALL NOT BE PERMITTED. Bars with kinks or bends not shown on the plans shall not be used. Reinforcing steel shall be accurately placed and secured against displacement by using annealed iron wire of not less than No. 18 gauge, or suitable clips at intersections. Where necessary, reinforcing steel shall be supported by metal chairs or spacers, pre-cast mortar blocks, or metal hangers. Reinforcing bars shall not be spliced at points of maximum stress. Splices, where permitted, shall be placed in the position and at the spacing shown on the plans with the tolerances specified in **ACI 301, Section 5.4**.
- h. Preventing Displacement. All reinforcing bars shall be supported and wired together to prevent displacement by construction loads or the placing of concrete. On ground, and where necessary, supporting concrete blocks shall be used. Over formwork, approved bar chairs and spacers shall be furnished.
- i. Materials for Accessories. Where the concrete surface will be exposed to the weather in the finished structure, the portions of all accessories in contact with the formwork shall be galvanized or shall be made of plastic. Where the concrete surface will be exposed to plant water, all accessories in contact with formwork shall be stainless steel or plastic.
- j. Mesh. Mesh shall lap at least 1-1/2 meshes, plus end extension of wires, but not less than 12 inches in slabs and shall extend across supporting beams and walls. In lieu of adequate support for mesh, one worker shall be designated to lift the mesh during placing of concrete

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.3 Structures

so that it is completely surrounded by concrete and not less than 2 inches above the bottom of slabs on ground or 1/2 inch above formwork.

- k. **Offsetting Bars.** Vertical bars in columns shall be offset to permit the bars to be adjacent and in contact at splices.
- l. **Splices.** All splices not shown on the drawings must have prior approval of the Local Entity Engineer.
- m. **No Bending.** Reinforcement shall not be bent after being partially embedded in hardened concrete.
- n. **Splice Laps.** Laps in tension splices shall be 36-bar diameters and 30-bar diameters in compression splices, or as noted.
- o. **Cover.** The minimum clear cover for reinforcing steel shall be as specified in **ACI 301, Section 5.5**, and as shown below, unless otherwise shown on the plans.

Bottom bars on soil bearing foundations and slabs:	3 inches
Bars adjacent to surfaces exposed to weather on earth backfill:	
Bars more than 3/4 inch in diameter	2 inches
Bars 3/4 inch or less in diameter	1-1/2 inches
Interior Surfaces: Slabs, walls, joints with 1-3/8 inches diameter or smaller bars	3/4 inches

4. Reinforcement Fabrication and Placing Tolerances.

- a. Bars used for concrete reinforcement shall meet the following requirements for fabricating tolerances:

Sheared length	+1 inch
Stirrups, ties	+1/2 inch
All other bends	+1 inch
- b. Bars shall be placed to the following tolerances:

Concrete cover to formed surfaces	+1/4 inch
Minimum spacing between bars	+1/4 inch
- c. Top bars in slabs and beams:

Members 8 inches deep or less	+1/4 inch
Members more than 8 inches but not over 2 feet deep	+1/2 inch
Members more than 2 feet deep	+1 inch
- d. Crosswise of members spaced evenly within 2 inches:

Lengthwise of members	+2 inches
-----------------------	-----------
- e. Bars shall be placed with the following minimum concrete cover, including tolerance unless noted on the drawings:

Concrete cast against earth	3 inches
Concrete exposed to earth or water	2 inches

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.3 Structures

Beams, girders, and columns	1-1/2 inches
Inside face of walls not exposed to earth or water	1 inch
Structural slabs not exposed to earth or water	3/4 inch

5. Placing Welded Wire Fabric. Wire fabric in crossspans and curb cuts shall be placed as shown in the plans and details. The fabric shall be fully supported on precast mortar blocks or other approved supports prior to placing the concrete.

22.3.7 Construction Requirements

A. Structural Concrete

1. Design Mix. The design mix and approval shall be in accordance with **CDOT Specifications Section 601.05**.
2. Batching. Measuring and batching of materials shall be in accordance with **CDOT Specifications Section 601.06**.
3. Mixing. Concrete shall be mixed in various type mixers according to **CDOT Specifications Section 601.07**.
4. Structural Cast-in-Place Concrete Forms.
 - a. General.
 - 1) Support of Loads. Design, erect, support, brace, and maintain form work to support vertical, lateral, static, and dynamic loads that might be applied until concrete structure can support such loads.
 - 2) Construction. Construct form work so concrete members and structures are of correct size, shape, alignment, elevation, and position.
 - 3) Quality. Maintain form work construction tolerances and surface irregularities complying with ACI 347 limits.
 - b. Conforming to Plans. Construct forms to sizes, shapes, lines, and dimensions as shown on the plans and to obtain accurate alignment location, grades, level, and plumb work in finished structures. Provide for openings, offsets, sinkages, keyways, recesses, moldings, rustications, reglets, chamfers, blocking, screeds, bulkheads, anchorages and inserts, and other features required in the Work. Use selected materials to obtain required finishes.
 - c. Joints. Butt all joints solidly and provide backup at joints to prevent cement paste from leaking.
 - d. Constructing for Removal. Fabricate forms for easy removal without hammering or prying against concrete surfaces. Provide crush plates or wrecking plates where stripping may damage cast concrete surfaces. Provide top forms for inclined surfaces where slope is too steep to place concrete with bottom forms only. Kerf wood inserts for forming keyways, reglets, recesses, and the like for easy removal.
 - e. Anchorage Devices. Set and build into form work anchorage devices and other embedded items required for other work that is attached to or supported by cast-in-place concrete. Use

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.3 Structures

setting drawings, diagrams, instructions, and directions provided by suppliers of items to be attached.

- f. Temporary Openings. Provide temporary openings for clean-outs and inspections where interior area of formwork is inaccessible before and during concrete placement. Securely brace temporary openings and set tightly to forms to prevent losing concrete mortar. Locate temporary openings in forms at inconspicuous locations.
- g. Chamfering. Chamfer exposed corners and edges as indicated, using wood, metal, PVC, or rubber chamfer strips fabricated to produce uniform smooth lines and tight edge joints.
- h. Provisions for Other Trades. Provide openings in concrete formwork to accommodate work of other trades. Determine size and location of openings, recesses, and chases from trades providing such items. Accurately place and securely support items built into forms.
- i. Cleaning and Tightening. Thoroughly clean forms and adjacent surfaces to receive concrete. Remove chips, wood, sawdust, dirt, or other debris just before placing concrete. Retighten forms and bracing before placing concrete, as required, to prevent mortar leaks and maintain proper alignment. All forms shall be oiled prior to each use.
- j. Checking Alignment. Before concrete placement, check the lines and levels of erected formwork. Make corrections and adjustments to ensure proper size and location of concrete members and stability of forming systems. During concrete placement, check formwork and related supports to ensure that forms are not displaced and that completed Work will be within specified tolerances.
- k. Forms Material. Forms shall be of wood, metal, or other material as specified below or approved by Local Entity Engineer. Approved flexible forms shall be used for construction where the radius is 100 feet or less. Unexposed surfaces shall have forms of No. 2 common (or better) lumber.
 - 1) Forms for Exposed Finish Concrete. Plywood, metal, metal-framed plywood faced, or other acceptable panel-type materials to provide continuous, straight, smooth, exposed surfaces. Furnish in largest practicable size to minimize number of joints.
 - 2) Forms for Unexposed Finish Concrete. Plywood, lumber, metal, or another acceptable material. Provide lumber dressed on at least two edges and one side for tight fit.
 - 3) Forms for Cylindrical Piers and Supports. Metal, glass-fiber-reinforced plastic, or paper or fiber tubes that will produce smooth surfaces without joint indications. Provide units with sufficient wall thickness to resist wet concrete loads without deformation.
 - 4) Carton Forms. Biodegradable paper surface, treated for moisture-resistance, structurally sufficient to support weight of plastic concrete and other superimposed loads.
 - 5) Form Release Agent. Provide commercial formulation form release agent with a maximum of 350 g/l volatile organic compounds (VOCs) that will

not bond with, stain, or adversely affect concrete surfaces and will not impair subsequent treatments of concrete surfaces.

- 6) Form Ties. Factory-fabricated, adjustable length, removable, or snap-off metal form ties designed to prevent form deflection and to prevent spalling of concrete upon removal. Provide units that will leave no metal closer than 1-1/2 inches to the plane of the exposed concrete surface.

Provide ties that, when removed, will leave holes no larger than 1 inch in diameter in the concrete surface.

- 7) Maximum Deflection. The maximum deflection of facing materials reflected in concrete surfaces exposed to view shall be 1/240 of the span between structural members. Suitable moldings or chamfer strips shall be placed in the corners of column, beam, and wall forms, except where specifically directed otherwise by the Local Entity Engineer.

- 8) Compensating for Deflections. Where necessary to maintain the specified tolerances, the formwork shall be cambered to compensate for anticipated deflections in the formwork due to the weight and pressure of the fresh concrete and construction loads.

- 9) Bracing. Positive means of adjustment (wedges or jacks) of shores and struts shall be provided, and all settlement shall be taken up during the concrete placing operation. The shores and struts shall be securely braced against lateral deflections.

- 10) Temporary Openings. These shall be provided at the base of column and wall forms, and at other points where necessary, to facilitate cleaning and inspection immediately before concrete is deposited.

- 11) Accessories. Forming accessories to be partially or wholly embedded in the concrete, such as ties and hangers, shall be a commercially manufactured type. Wire is not acceptable. The portion remaining within the concrete shall leave no metal within one inch of the surface when the concrete is exposed to view. Spreader cones on ties shall not exceed 1 inch diameter. Embedded ties used in water containment structures shall have approved water seal washers.

1. Form Removal Timing. Forms shall not be disturbed until the concrete has adequately cured. The Developer or his superintendent shall be present at the time forms are removed and shall be responsible for the safety of this operation at all times. It is suggested that the minimum time between placing concrete and removal of forms be less than the following:

Item Poured	Minimum Time to Removal
Walks, Curb and Gutter	6 hours
Side forms for footings and slabs	12 hours
Side forms for walls, beam, and columns	24 hours

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.3 Structures

Forms under structural beams and slabs require shoring 7 days or when concrete has reached 2/3 of 28-day field design strength as indicated by compressive strength tests on field cured specimens.

m. Removal of Forms and Reshoring.

- 1) Non-Weight Bearing. Form work for columns, walls, sides of beams, and other parts not supporting the weight of the concrete may be removed as soon as the concrete has hardened sufficiently to resist damage from removal operations. See **Section 22.3.7 A.4.1.**
- 2) Weight Bearing. Form work for beam soffits, slabs, and other parts that support the weight of concrete shall remain in place until the concrete has reached its specified 28-day strength, unless otherwise specified or permitted.
- 3) Ability to Carry Loads. Forms shall not be removed in any case until the concrete has had time to set sufficiently to carry the deadloads and any construction loads it has to sustain, and in no case will the forms be removed until permission is obtained from the Engineer or his representative.
- 4) Facing Material. When shores and other vertical supports are so arranged that the form-facing material may be removed without loosening or disturbing the shores and supports, the facing material may be removed at an earlier age as specified or permitted. The shores and supports shall remain in place until the concrete has reached its specified strength, unless otherwise specified or permitted. See **Section 22.3.7 A.4.1.**
- 5) Reshoring. Reshoring for the purpose of early form removal shall be performed, so that at no time will large areas of new construction be required to support their own weight. While reshoring is underway, no live loads shall be permitted on the new construction. Reshores shall be tightened to carry their required loads, but they shall not be over tightened so that the new construction is over-stressed. Reshores shall remain in place until the concrete has reached its specified 28-day strength, unless otherwise specified or permitted.
- 6) Removal Strength. This shall be based upon test cylinder strengths, as specified in **Chapter 23, Street Inspection and Testing Procedures**, or pullout tests in accordance with ASTM C900, and upon the approval of the Local Entity Engineer.

n. Refer to **Section 22.3.7 A.4** for construction, fabrication, type, cleaning, and removal of forms.

5. Permanent Steel Bridge Deck Forms. Permanent steel bridge deck forms shall be installed according to **CDOT Specifications Section 601.10.**
6. Falsework. Falsework shall be designed, constructed, and removed according to **CDOT Specifications Section 601.11.**

7. Placement. The placement of concrete, conditions, holes, and joints shall be in accordance with **CDOT Specifications Section 601.12**.
8. Curing Concrete Other Than Bridge Deck. Refer to **Section 22.4.3 C**.
9. Finishing.
- a. Ordinary Surface Finish. All concrete surfaces shall be given a Class 1 finish per **CDOT's Class 1 Finish, Section 601.14(b)** unless additional finish classes are specified by the plans for designated surfaces.
- b. Class 3, CDOT Class 5, Masonry Coating Finish. Refer to **CDOT**
- c. Specifications Section 601.14(b).
10. Bridge Deck Placing. Concrete shall be placed in accordance with **CDOT Specifications Section 601.12** except where there are conditions and procedures in accordance with **CDOT Specifications Section 601.15**.
11. Bridge Deck Curing. Concrete bridge decks, including bridge curbs shall be cured according to **CDOT Specifications Section 601.16**.
12. Waterproofing. Installation of waterproofing membrane over a prepared concrete bridge shall be in accordance with **CDOT Specifications Sections 515.03** through **515.07**.
13. Waterstops. Waterstops of appropriate size and type shall be installed according to **CDOT Specifications Section 518.03**.

B. Structural Steel

1. General. Welding, fabrication, and construction of steel structures shall conform to **AASHTO's LRFD Bridge Construction Specifications**, latest edition, **AASHTO's Standard Specifications for Highway Bridges**, latest edition, and **CDOT Specifications Section 509.02**.
2. Fabrication. General fabrication, welding, shop assembly, connections, cleaning and painting, galvanizing, and marking of steel structures shall conform to **CDOT Specifications Sections 509.19** through **509.25**.
3. Construction. Erection, connections, field cleaning, and painting of steel structures shall be in accordance with **CDOT Specifications Sections 509.27** through **509.29**.

C. Structural Plate

1. Fabrication. Fabrication of structural plate structures shall be in accordance with **CDOT Specifications Section 510.03**.
2. Construction. Erection of structural plate structures shall be in accordance with **CDOT Specifications Section 510.05**.

D. Timber

1. General. Treated and untreated timber shall be erected according to **CDOT Specifications Section 508.06**.
2. Holes and Bolts. Holes bored and drilled and bolt accessories shall be installed according to **CDOT Specifications Section 508.07**.
3. Painting. All old and new timber, handrails, posts, and parts shall be painted in accordance with **CDOT Specifications Section 508.08**.

E. Bearing Device

1. Fabrication. Fabrication of bearing devices shall apply to three types of devices and be in accordance with **CDOT Specifications Sections 512.03 through 512.05**. Bearing devices shall include hardware and provide for movement in accordance with **CDOT Specifications Section 512.06**.
2. Construction. Bearing devices are to be installed, protected, certified, and approved according to **CDOT Specifications Sections 512.09 through 512.15**.

F. Pipe Railing

Pipe railing shall be installed and painted according to **CDOT Specifications Section 514.03**.

G. Cold Weather Requirements

Prior to placing concrete, ice, snow and frost shall be removed from the forms and subgrade. In no case shall concrete be placed against frozen ground or against ground containing frost. Except by specific written authorization, concrete shall not be placed unless the air temperature adjacent to the concrete placement is 30°F and rising and placing shall cease when the air temperature adjacent to the concrete placement falls below 40°F as determined by the Local Entity Engineer. When concrete placement is permitted during cold weather, the temperature of the mix shall not be less than 50°F nor more than 90°F at the time of placement. Aggregates or water shall not be heated to a temperature exceeding 150°F. Materials containing frost or lumps of frozen material shall not be used. If heated mixing water and/or an accelerator are used, the above limits may be waived only with written permission of the Local Entity Engineer. When concrete is placed in cold weather and the air temperature is expected to drop below 35°F, a suitable blanketing material shall be at the job site during placement. At any other time when the air temperature is expected to reach the freezing point for a period of 72 hours after placement, the work shall be blanketed for protection of the concrete.

22.4 NON-STRUCTURAL CONCRETE

Non-structural concrete includes curb, gutter, walks, driveways, crosspans, and ramps.

22.4.1 General

A. Protection

It shall be the Developer's responsibility to protect new concrete from damage with appropriate methods. For areas exposed to vehicular traffic, the concrete shall be protected until 80% of required concrete strength is achieved.

B. Damaged Concrete

Damaged concrete shall be repaired, removed and/or replaced according to **Chapter 25, Reconstruction and Repair**.

C. Sequence of Construction

1. Sanitary and Storm Sewer. All curb, gutter, crosspans, and sidewalk (where attached) shall be constructed after installation of sanitary sewer, water, and storm sewer mains, laterals, and service lines have been installed and properly compacted in accordance with these specifications.
2. Water Mains. Water mains which cross curb, gutters, attached walks, and driveways shall also be installed and properly compacted prior to installation of said curb, gutter, attached walks, and driveway approaches.
3. Water Service, Valve Boxes, and Manholes. Water service lines may be installed after curb, gutter, and attached walks have been in place at least 7 days. Water valve boxes and manholes shall be adjusted to final grade after installation of curb and gutter.
4. Electrical Services. Electrical services shall be installed after water services but prior to installation of curb radii except where previous arrangements for use of conduit have been made and approved by the Local Entity's Light and Power department.

22.4.2 Materials and Methods

A. Concrete

Concrete shall be composed of cement, coarse and fine aggregate, water, and entrained air. The concrete shall contain a minimum of 6 sacks of cement per cubic yard or an equivalent cement/fly ash combination not to exceed 20 percent cement replacement (when approved), a maximum of 6 gallons of water per sack of cement, an air content between 5 percent and 8 percent by volume, and a maximum coarse aggregate size of 1-1/2 inches. Any admixture (except air entraining agent) must be approved by the Local Entity Engineer.

1. Concrete Strength. The finished concrete shall have a minimum 28-day compressive strength of 4000 psi.
2. Water/Cement Ratio. The concrete shall have a maximum water/cement ratio of 0.45.

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.4 Non-Structural Concrete

3. Fine Aggregate.

- a. Composition. Fine aggregate shall be natural sand composed of clean, hard, durable, uncoated grains, preferably of siliceous materials.
- b. Deleterious Substances. The maximum percentage of deleterious substances shall not exceed the following values:

Substance	Maximum Percentage
Material finer than 200 mesh sieve	3% by weight
Shale	1% by weight
Coal and lignite	0.25% by weight
Clay lumps	1% by weight
Other deleterious substances	2% by weight
Sum of all above shall not exceed	5% by weight

All fine aggregate shall be free from injurious amounts of alkali and organic impurities.

- c. Gradation. Fine aggregate shall be well graded and conform to **AASHTO M6** as shown in **CDOT Specifications Section 703, Table 703-1**.

4. Coarse Aggregate.

- a. Composition. Coarse aggregate shall consist of crushed limestone, trap rock, granite, washed gravel, or other approved inert materials having clean, hard, strong, durable pieces, free from adherent coating, and conforming to the requirements or these specifications.
- b. Deleterious Substances. The maximum percentage of deleterious substances shall not exceed the values listed in [Table 22-3](#)~~Table 22-3~~[Table 22-3](#).
- c. Gradation. Course aggregate shall be well graded and conform to AASHTO M43 and as shown in CDOT Specifications Section 703, Table 703-1.
- 5. Fly Ash, Water, Admixtures. Refer to **Sections 22.5.5 A.322.5.6 A.6, 22.5.5 A.422.5.6 A.7, and 22.5.5 A.522.5.6 A.8**.

Formatted: Font: Bold
Formatted: Font: Bold

B. Job-Mixed Concrete

Job-mixed concrete shall be mixed in a drum-type mixer which shall conform to the Standards of the Mixer Manufacturers Bureau of the Associated General Contractors of America.

- 1. Mixing and Discharging. The mixer shall be capable of combining the aggregates, cement, and water into a thoroughly mixed and uniform mass within the specified time and discharge the material without segregation. The entire contents of the drum shall be discharged before recharging. The volume of the mixed materials per batch shall not exceed the manufacturer's rated capacity of the mixer. Mixers must be kept clean of hardened concrete.

2. Mixing Time and Rate of Revolutions. The mixing of each batch shall continue for not less than one minute after all materials, except water, are in the drum. All mixing water shall be introduced before 1/4 of the mixing time has elapsed. The mixer shall rotate at the rate recommended by the manufacturer, but not less than 14 or more than 20 revolutions per minute. When additional water is added, another 30 revolutions of the drum will be required.
3. Cement Type. When concrete is mixed at the site, cement must be Type IA or IIA. The addition of any admixture at the job site is prohibited.

C. Ready-Mixed Concrete

Ready-mixed concrete shall be proportioned, mixed, and transported in accordance with the current ASTM Specifications for Ready-Mixed Concrete (Designation C-94). Delivery of central-mixed concrete shall not be made in non-agitating equipment.

22.4.3 Construction

A. Concrete Finishing

1. General.
 - a. Exposed faces of curbs and sidewalks shall be finished to true line and grade as shown on the plans. The surface shall be floated to a smooth, but not slippery finish.

After completion of finish and before concrete has taken its initial set, all edges in contact with the forms shall be edged with an edger.
 - b. Sprinkling of the surface with water, to facilitate finishing, shall not be permitted.
2. Finish Types.
 - a. Broom Finish. All concrete curb-gutter and sidewalk, unless otherwise specified.
 - b. Float Finish. All access ramps and transitions shall be hand-finished, with a wood or magnesium float.
 - c. Exposed Aggregate for median surface.
3. Markings.
 - a. Appurtenances. In Ft. Collins (city limits), concrete used in curb-gutter, sidewalk, curb cuts, driveways, inlets, bicycle paths, retaining walls, and slope paving shall have the name of the Concrete Contractor and the year of construction impressed therein, using letters not less than 1 inch high and 3/8 inch deep. Impressions shall be made in concrete at the beginning and end of each pour.
 - b. Utility. Impressions (similar to appurtenances) delineating the location of water and sewer, (S for sanitary sewer, C for clean out, + for water, with the top of the + pointing to the water stop box), shall be located on the curb face at all service crossings.
 - c. Structures. Structures shall have the year constructed impressed therein, using letters 3 inches high, 1-1/2 inches wide and 3/8 inches deep.

B. Repairs

1. Defective Areas. If, after stripping of forms, any concrete is found to be not formed as shown on the drawings, or is out of alignment or level, or shows a defective surface, it shall be considered as not conforming with these Standards. The defective area shall be removed and replaced by the Developer at his expense.
 2. Sidewalk Areas. For Loveland (GMA and city limits), bolt holes, tie-rod holes, and minor imperfections, for sidewalks only, as approved by the Local Entity Engineer, shall be filled with dry-patching mortar.
- a. Dry-patching Mortar shall be composed of one part Portland cement to two parts of regular concrete sand (volume measurement), and water. Use only enough water that the mortar will stick together upon being molded, after the ingredients are mixed thoroughly. These mortar mix proportions are approximate.
- b. Placing Mortar. Mortar repairs shall be placed in layers and thoroughly compacted by suitable tools. Care shall be taken in filling rod and bolt holes so that the entire depth of the hole is completely filled with compacted mortar.

C. Concrete Curing

1. General. Protect freshly placed concrete from premature drying and excessive cold or hot temperatures as well as rain, flowing water, and mechanical injury. In hot, dry, and windy weather, protect concrete from rapid moisture loss before and during finishing operations with an evaporation-control material.

Start initial curing as soon as free water has disappeared from concrete surface after placing and finishing.
2. Materials. Refer to the Materials Specification in CDOT 601.13 for concrete curing methods.
3. Curing Methods. Cure concrete by one of the following methods:
 - a. Liquid Membrane Curing Compound. Apply pigmented curing compound to exposed interior slabs and on exterior slabs, walks, and curbs as soon as final finishing operations are complete. Apply uniformly in continuous operation, according to manufacturer's directions, and at a rate of 150 sq ft per gallon for all concrete. The compound shall be kept agitated to prevent the pigment from settling.
 - b. Moisture Retaining Cover Curing. This curing approach is optional in Loveland (GMA and city limits) only. Cover concrete surfaces with moisture-retaining cover (polyethylene sheets) for curing concrete, placed in widest practicable width, with sides and ends lapped at least 12 inches and sealed by waterproof tape or adhesive. Immediately repair any holes or tears during curing period, using cover material and waterproof tape.

D. Cold Weather Requirements

Refer to 22.3.7 G.

E. Joints

1. Tooled Joints. Transverse joints shall be located at intervals of 10 feet in curbs, gutters, and crosspans. When combination curb, gutter, and walk are used, the joint shall be continuous through all three elements with a maximum spacing of ten feet. The joints shall be initially cut a minimum of one-third the thickness of the concrete. For detached sidewalks, the tooled joint spacing shall equal the sidewalk width.
2. Expansion Joints. Expansion joint material shall be installed every 500' in long runs and between new structure slabs and existing concrete slabs, where called for and around fire hydrants, poles, inlets, sidewalk underdrains, midblock ramps, radius points at intersections, and other fixed objects, i.e. joints with existing sidewalk slabs and curbs. Expansion joint material must be set vertical and installed in accordance with the CDOT specification titled M&S Standards for Concrete Pavement Joints. The joint shall be edged with a suitable edging tool and sealed in accordance with CDOT Section 412.18

F. Backfilling

The space adjoining the concrete shall be backfilled with suitable material, properly compacted, and brought flush with the surface of the concrete and adjoining ground surface no earlier than 7 days after concrete placement, unless otherwise approved by the Inspector.

In embankments, the backfill shall be level with the top of the concrete for at least 2 feet and then sloped to meet existing grade. Maximum slope shall be 4:1. For walks detached from the curb, the space between the curb and walk shall be backfilled on a straight line from the top of walk to the top of curb.

G. Opening to Traffic

It shall be the Developer's responsibility to protect new concrete and repairs from damage with appropriate methods. For areas to be exposed to traffic, the concrete shall be protected until 80% of required concrete strength is achieved.

H. Warranty

The Developer shall guarantee curb, gutter, walks, driveways, and crosspans after completion against defective workmanship, materials and vandalism. The determination of the necessity during such guarantee period for the Developer to repair said curb, gutters, walks, driveways or crosspans, or any portion thereof, shall rest entirely with the Local Entity Engineer whose decision upon the matter shall be final and binding upon the Contractor. Refer to **Chapter 24, Acceptance Procedures and Record Drawings/Warranty**, for additional information.

I. Initial and Final Acceptance

Upon substantial completion and upon written request of the Developer, the Local Entity Engineer shall, with the Developer, physically examine the work and/or phase of the work. The Local Entity Engineer shall issue written initial acceptance of the

work with a “punch list” of deficiencies to be completed within 30 days and prior to final acceptance. If no deficiencies are found, the Local Entity Engineer shall issue a written final acceptance of the work. Refer to **Chapter 24, Acceptance Procedures and Record Drawings/Warranty**.

22.4.4 Tunneling or Boring Under Curb, Gutter, Walks, and Pavements

A. General

Excavate surfaces under walks and pavements to indicated cross sections, elevations, and grades on plans.

B. Borings

Boring for utilities shall be permitted if approved by the Local Entity Engineer.

1. Less Than 6 Inches. For openings less than or equal to 6 inches in diameter, bore holes shall be filled with patching material (cold mix is not acceptable) to prevent entry of moisture. Patching material used shall be in all cases compatible with the existing surface. Subgrade shall be replaced with flowable fill to provide necessary support to the surface. The sealing of bore holes is the responsibility of the Contractor or persons making the bore.
2. Greater Than 6 Inches. For openings greater than 6 inches in diameter, the limits of repair shall be identified in the field.
3. Finished Condition. The completed job shall be flush with the surrounding pavement and have no indentations, pockets, or recesses that may trap and hold water.

22.5 PAVEMENT

~~22.5.1~~ General

~~During the construction of pavement, all required signal loops must be installed between asphalt layers or placed in concrete during the pour. The Local Entity is responsible for loop installation. The Developer is responsible for coordination with the Local Entity and will give 48 hours of notice prior to commencement of construction. We are reviewing this Process~~

Formatted: Indent: Left: 0.5", No bullets or numbering

~~22.5.2~~ ~~22.5.1~~ Fill

Cavities that are a result of excavation and areas deficient in grade shall be brought to grade with fill material. All imported fill material shall be tested in accordance with **Chapter 23, Street Inspection and Testing Procedures**.

A. Engineered Fill

Subbase or base materials. See Sections ~~22.5.3~~ ~~22.5.4~~ and ~~22.5.4~~ ~~22.5.5~~ ~~22.5.5~~.

Formatted: Font: Not Bold

Formatted: Font: Not Bold

~~22.5.3~~ **22.5.2 Subgrade and Roadbed**

A. General

Subgrade material shall conform to the lines, grades, cross-sections, and thickness shown on the approved plans and shall be finished and maintained in an acceptable condition at least one day's progress in advance of base construction.

B. Subgrade Approval

1. Notification. Notify the Local Entity Engineer when excavations have reached required subgrade.
2. Inspection. See Chapter 23, Street Inspection and Testing Procedures.
3. Reconstruction. See Chapter 23, Street Inspection and Testing Procedures.

C. Subgrade Preparation

1. Preparation Conditions. Work shall not occur on the subgrade in freezing conditions, or when the subgrade is frozen.
2. Compaction. The subgrade shall be free of organic material and shall be deep-plowed to a minimum depth of 12 inches, moisture-treated to within 2 percent (or as specified on the plans or geotechnical report) of optimum moisture content, thoroughly mixed, and replaced and compacted to 95% maximum standard proctor in 6-inch lifts.
3. Testing. See **Chapter 23, Table 23-1 Material Testing**.
4. Final Proof-Rolling. After the subgrade has been compacted, tested, and found to meet specifications, the entire subgrade shall be mechanically proof-rolled with a heavily loaded vehicle to ensure uniformity of the subgrade. The vehicle must have a loaded GVW of 50,000 pounds with a loaded single axle weight of at least 18,000 pounds and a tire pressure of 90 psi. Subgrade which is pumping or deforming under loading must be reworked, replaced or otherwise modified, to form a smooth, stable, non-yielding base for subsequent paving courses. The Local Entity Engineer shall be notified at least 24 hours before final proof-rolling. All proof rolls shall be observed and approved by an Inspector.
5. Preparation of Cut Surfaces and Undisturbed Areas. Subgrade surfaces below excavated areas such as cut areas and undisturbed areas require additional preparation. Unless otherwise approved by the Local Entity Engineer, said subgrade shall be scarified to a depth of 12-inches, wetted or aerated as needed, and compacted to 95% maximum standard proctor dry density (AASHTO T-99) at +/-2% of optimum moisture content for cohesive soils or +/-3% for non-cohesive soils.
 - a. Expansive soils, refer to **Chapter 10**.
6. Acceptance. See **Chapter 23, Street Inspection and Testing Procedures**.

D. Subgrade Protection

During construction, subgrades and excavations shall be kept shaped and drained. Ditches and drains along the subgrade shall be maintained to drain effectively at all times. Where ruts occur in the subgrade, the subgrade shall be brought to grade, reshaped, and recompacted prior to placing of subbase material. The storage or stockpiling of materials on the subgrade will not be permitted. No base course shall be laid until the subgrade has been inspected and approved. Under no circumstances shall base or pavement material be placed on a muddy or unstable subgrade.

E. Soil Stabilization

1. **General.** For new construction, soil stabilization shall extend to back of curb for detached walk and to back of walk for attached walk.
2. **Lime Stabilization.** This section specifies requirements for design, materials, and construction of lime-stabilized subgrades. This section is applicable to stabilizing fine-grained soils (clays and silts) only. It is not applicable to stabilizing sands and gravels used as bases or subgrades.

- a. **General.** The purpose of lime stabilization is to improve the subgrade quality of a clay soil by increasing its strength and reducing its swell-shrink potential during wet-dry cycles.
- b. **Materials.** The material for lime treated subgrade consists of a mixture of native or imported soils, hydrated or quick lime and water, as outlined by **ASTM Specification C977**. Hydrated lime shall conform to the requirements of **ASTM C 207-79**, Type N. In addition, the residue retained on a 200 mesh sieve shall not exceed 10 percent when determined in accordance with **ASTM C 110**. Drying of the residue in an atmosphere free from carbon dioxide will not be required.

The materials to be used in construction shall be tested and a mix design submitted to the Local Entity Engineer for approval. See **Chapter 23, Street Inspection and Testing Procedures**, concerning mix design report.

- c. **Preparation and Application.** The surface of the roadbed shall be graded to the established lines, grades, and cross sections as shown on the plans. The prepared roadbed shall be scarified to the depth and width required for the subgrade stabilization. The material thus obtained shall be pulverized. Application, mixing, and finishing shall be in accordance with **CDOT Specification Sections 307.05 through 307.09**.
- d. **Design and Testing.** A site-specific lime-stabilization design is required prior to construction and based on a soil report with additional testing required. See **Chapter 5, Soils Investigations and Report**. The design shall be prepared by a Colorado Registered Professional Engineer competent in the field of geotechnical engineering and shall be included in the Pavement Design Report as required in **Chapter 10, Pavement Design and Technical Criteria**. Testing shall verify that projected “R” values were achieved.
- e. **Mix Design Approval.** To be approved, the mix shall have a minimum 7-day compressive strength of 160 psi. In addition, the plasticity index of the treated soil shall not exceed 6. The minimum acceptable hydrated lime content shall be 4 percent by weight.

Only mix designs approved by the Engineering Division shall be used. Approvals are required on a project basis prior to issuing construction permits. Minimum in-place thickness for this material shall be 8 inches.

f. Pavement Design.

- 1) Flexible Pavement Over Stabilized Subgrade. The ~~86~~-AASHTO Guide for the Design of Pavement Structures is the basis of the Local Entity's design procedure. For lime-stabilized subgrades with a minimum compressive strength of 160 psi, a strength coefficient of 0.14 shall be used in the layer-thickness equation. Refer to **Chapter 10, Pavement Design and Technical Criteria**, for the flexible pavement design procedure and show calculations in the pavement design report.
- 2) Rigid Pavement Over Stabilized Subgrade. The appropriate design nomographs for rigid pavement referenced in **Chapter 10, Pavement Design and Technical Criteria** shall be used to determine slab thickness. Evidence supporting a total modulus of subgrade reaction for the untreated subgrade and the lime-stabilized layer shall be provided.
3. Fly Ash Stabilization. This item shall consist of treating the subgrade or existing base, by pulverizing, adding Class C fly ash, and mixing and compacting the mixed material to the required density. This item applies to natural ground or embankment and shall be constructed as specified herein and in conformity with the typical sections, lines and grades as shown on the plans or as established by the Engineer.

a. Materials

- 1) Fly Ash. Fly Ash shall meet **ASTM C 618** for Class C Fly Ash.
- 2) Water. The water used in the stabilization mixture shall be potable.

b. Construction Requirements

c. Equipment

- 1) The machinery, tools and equipment necessary for proper execution of the work shall be on the project and approved by the Local Entity Engineer prior to the beginning of construction operations.

All machinery, tools, and equipment used shall be maintained in a satisfactory and workmanlike manner.

- a) Fly ash shall be furnished in trucks. Each truck shall have the weight of fly ash recorded on certified scales.

d. Construction Methods

- a) General. It is the purpose of this specification to secure a completed course of treated material which contains a uniform fly ash/soil mixture with no loose or segregated areas, has a uniform density and

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.5 Pavement

moisture content, is well bound for its full depth, and has a smooth surface suitable for placing subsequent courses. It shall be the responsibility of the Developer to regulate the sequence of work; to process a sufficient quantity of material to provide full depth as shown on the plans; to use the proper amounts of fly ash; to maintain the work and to rework the courses as necessary to meet the above requirements.

- b) Preparation of Subgrade. Before other construction operations have begun, the subgrade shall be graded and shaped to enable the fly ash treatment of materials in place, in conformance with the lines, grades, and thickness shown on the plans.
- c) Application. The fly ash shall be spread by a method approved by the Local Entity Engineer at the rates shown on the plans or as directed by the Local Entity Engineer. Fly ash shall not be applied when wind conditions, in the opinion of the Local Entity Engineer, are such that blowing fly ash becomes objectionable to traffic or adjacent property owners.

During final mixing, the materials shall be sprinkled, as directed by the Local Entity Engineer, until the proper moisture content has been secured. However, initial mixing after the addition of fly ash will be accomplished dry, or with a minimum of water, to prevent fly ash balls.

Final moisture content of the mix, prior to compaction, shall not exceed the optimum moisture content of the mix by more than 2 percent, nor less than optimum by more than 2 percent. Should the natural moisture content of the soil be above the specified range, aeration of the soil may be required prior to addition of the fly ash.

- d) Mixing. The soil and fly ash shall be thoroughly mixed by approved road mixers or other approved equipment. The mixing shall continue until, in the opinion of the Local Entity Engineer, a homogeneous, friable mixture of soil and fly ash is obtained, free from all clods or lumps.

Water required to achieve the specified moisture content for the mixture should be added after initial mixing. There shall be a 6 inch overlap between passes to assure a consistent mix.

- e) Compaction. Compaction of the mixture shall begin immediately after mixing of the fly ash and shall be completed within two hours following addition of water to the fly ash. The material shall be sprinkled as necessary to maintain the optimum moisture.

Compaction of the mixture shall begin at the bottom and shall continue until the entire depth of mixture is uniformly compacted to the specified density. All non-uniform (too wet, too dry, or insufficiently treated) areas

that appear shall be corrected immediately by sprinkling and rolling. The surface of the course shall be maintained in a smooth condition, free from undulations and ruts, until work is placed thereon of the work is accepted.

The stabilized section shall be compacted to the extent necessary to provide the density specified in [Table 22-1](#).

Formatted: Font: Bold

Formatted: Font: Bold

**Table 22-1
Required Density for Stabilized Compaction**

Description	Density
For fly ash treated subgrade, existing subbase or existing base that will receive subsequent subbase or base courses.	Not less than 95% maximum dry density (ASTM D 698)
For fly ash treated base that will receive surface course.	Not less than 97% maximum dry density (ASTM D 698)

In addition to the requirements specified for density, the full depth of the material shown on the plans shall be compacted to the extent necessary to remain firm and stable under construction equipment. After each section is completed, tests as necessary may be required by the Engineer.

If the material fails to meet the density requirements, the Engineer may require it to be reworked as necessary to meet those requirements or require the Developer to change construction methods to obtain required density on the next section. Throughout this entire operation the shape of the course shall be maintained by blading, and the surface, upon completion, shall be smooth and in conformity with the typical section shown on the plans and to the established lines and grades. Blading should be terminated within two hours after blending of the fly ash.

Should the material, due to any reason or cause, lose the required stability, density or finish before the next course is placed, or the work is accepted, it shall be reprocessed, re-compacted, and refinished at the sole expense of the Developer. Reprocessing shall follow the same pattern as the initial stabilization, including the addition of fly ash.

- 2) Finishing, Curing, and Preparation for Surfacing. After the final layer or course of the treated subgrade, subbase or base has been compacted, it shall be brought to the required lines and grades in accordance with the typical sections.
 - a) The resulting base surface shall be thoroughly rolled with a pneumatic tire roller and “clipped,” “skinned” or “tight bladed” by a power grader to a depth of approximately ¼ inch, removing all loosened stabilized material from the section. Re-compaction of the loose material should not be attempted.

The surface shall then be thoroughly compacted with the pneumatic roller, adding small increments of moisture as needed during rolling. If plus No. 4 aggregate is present on the surface of the mixture, one complete coverage of the section with the flat wheel roller shall be made immediately after the “clipping” operation.

When directed by the Local Entity Engineer, surface finishing methods may be varied from this procedure provided a dense, uniform surface, free of surface compaction planes, is produced. The moisture content of the surface material must be maintained within the specified range during all finishing, and shall proceed in such a manner as to produce, in not more than two hours, a smooth, closely knit surface, free of cracks, ridges or loose material conforming to the crown, grade and line shown on the plans.

- (1) After the fly ash treated course has been finished as specified herein, the surface shall be protected against rapid drying in a thorough and continuously moist condition by sprinkling for a period of not less than three days, or until the surface or subsequent courses are placed. We are looking at this
- 3) Other Materials for Stabilization. Other methods of stabilization may be considered only with sufficient supporting data submitted by the Designer for the proposed method.

Formatted: Font color: Red, Not Highlight

Formatted: Not Highlight

Formatted: Font color: Red, Not Highlight

Formatted: Not Highlight

F. Subgrade Surface Tolerance

Variations from the subgrade shall not be more than 1 inch in soil. Where bituminous asphalt or Portland cement concretes are to be placed directly on the subgrade, the subgrade plane shall not vary more than 1/2 inch.

22.5.4 22.5.3 Subbase

A. Materials

Subbase material shall be well mixed, free of organic matter, and lumps or balls of clay, and shall consist of sound aggregate particles and suitable filler or binding materials which, when placed and compacted, will result in a firm, dense, unyielding foundation. Subbase material need not be crushed, but may be of the pit run variety, providing it is graded according to **CDOT Table 703-2, Class 1 Aggregate Base Course**. The plasticity index shall not exceed 6 when the aggregate is tested in accordance with **AASHTO T89** and **T90** respectively. “R” value shall be a minimum of 50 and the test loss for the Los Angeles Abrasion test (**AASHTO M147**) shall be less than 50 percent.

Deviations from the CDOT gradation limits will be permitted when approved by the Local Entity Engineer for unpaved roads, where it can be adequately demonstrated that the proposed subgrade material can fulfill the intent of these specifications.

B. Application

Subbase shall be deposited and spread, without particle segregation, in loose layers not to exceed 6 inches in depth. Each layer shall be thoroughly and individually compacted to 95 percent standard proctor (**AASHTO T 99**) density. Wetting or aerating and rolling of the material shall be required when ordered by the Engineer. Subbase shall not be placed on soft, spongy, or frozen subgrade or other subgrade, the stability of which, in the opinion of the Local Entity Engineer, is unsuitable.

C. Surface Tolerance

The prepared surface of the subbase shall not vary from the established grade by more than one inch.

~~22.5.5~~ **22.5.4 Base Course**

This section covers furnishing, placing, and watering gravel or stone to provide a firm and stable foundation for subsequent construction. The base course shall be constructed on a previously constructed subgrade in accordance with the lines, grades, quantity requirements, and the typical cross-sections shown on the plans.

A. General

Base material shall conform to the lines, grades, cross-sections, and thicknesses shown on the approved plans and shall be finished and maintained in an acceptable condition at least one day's progress in advance of placing prime coat or paving material.

B. Aggregate Base Course Material

Base material shall consist of hard, durable particles or fragments of stone or gravel crushed to the required sizes. Material shall contain an appropriate quantity of sand or other finely-divided mineral matter which conforms to the requirements of **AASHTO M 147**, and to **Section 703.03, CDOT Standard Specifications Class 5 or Class 6 Aggregate Base Course**. In addition, the material must have an R-value of 72 or greater, and must be moisture stable. When produced from gravel, not less than 60 percent by weight of the aggregate retained on a No. 4 sieve shall consist of particles having at least one fractured face. Base material shall be free from vegetable matter and lumps or balls of clay and when placed and compacted will result in a firm, dense, unyielding foundation. The Local Entity Engineer may approve recycled asphalt or concrete pavement.

Coarse aggregate shall show a loss of not more than 50 percent when tested in accordance with **AASHTO Standard Method of Test for Abrasion of Coarse Aggregate** by use of the Los Angeles Machine, Designation: AASHTO T-96 (AASHTO M 147).

1. Approval of Sources. Only aggregate from the Local Entity approved sources shall be used. Refer to **Chapter 23, Street Inspection and Testing Procedures**.

(Approval of sources will, at a minimum, consist of supplying documented gradation, Atterberg limits, and R-value testing on an annual basis).

C. Cement Treated Aggregate Base Course Material

This material shall consist of a mixture of aggregate materials, Portland cement, and water as outlined in **Section 308 of the CDOT Standard Specifications**, latest version. Acceptable aggregates include **CDOT Classes 4, 5, and 6**. Other aggregates may be used, if previously approved by the Local Entity Engineer. The materials to be used in construction shall be tested and a mix design submitted to the Local Entity Engineer.

1. Mix Design Approval. To be approved, the mix shall have a 7-day compressive strength of at least 650 psi, and no more than 1000 psi. The minimum acceptable cement content shall be 5 percent by weight.

Only mix designs approved by the Local Entity Engineer shall be used. Approvals are required on a project basis, or an annual basis for suppliers, prior to issuing construction permits.

D. Application

Base material shall be deposited and spread without particle segregation in loose layers not to exceed 6 inches in depth. Each layer shall be thoroughly and individually compacted to 95 percent standard Proctor (**AASHTO T-99**) density. Wetting or aerating and rolling of the material shall be required as ordered by the Local Entity Engineer, following review of all field test results. No base course shall be placed upon a soft, spongy, or frozen subgrade or other subgrade, the stability of which, in the opinion of the Local Entity Engineer, is unsuitable.

E. Surface Tolerance

The prepared surface of the base shall not vary above or below the established grade by more than 1/2 inch.

F. Soil Sterilization

Soil sterilization shall be applied under all new paving. The sterilization agent shall be a pre-emergent herbicide, soluble, dispersible, or mixable in water and nontoxic to humans when applied per the manufacturer's recommendations. The agent shall be active for one year after application. The applicator shall be certified by the U.S. Environmental Protection Agency and licensed in the State of Colorado as a pesticide applicator and shall be held responsible for any damage to plant growth outside of the roadway or to pavement where such damage is attributable to carelessness or improper application of the agent. Care shall also be taken to prevent contamination of surface waters.

~~22.5.6~~ 22.5.5 **Portland Cement Concrete Pavement**

A. Materials

This material shall consist of a mixture of coarse and fine aggregates, Portland cement, water, and other materials or admixtures as required. Colorado Department of Transportation Class “P” or “AX” mix may be used. The only alternatives to “P” or “AX” shall be according to **Section 412.03 of CDOT Standard Specifications**. Other high-early strength concretes may be used only where special conditions warrant, subject to written approval by the Local Entity Engineer.

1. Portland Cement. Portland cement shall comply with the Colorado Department of Transportation requirements. The type of cement shall be Type II, unless sulfate conditions necessitate otherwise. **Table 2.2.3** in **Chapter 2.2** of **ACI 201** indicates recommendations for sulfate resistance.

~~2.~~ Fine Aggregates. Fine Aggregates shall meet Colorado Department of Transportation Section 703.01 requirements and gradation as shown in CDOT Table 703-1 and **Table 22-2**.

~~3.~~ Table 22-2

~~3-2.~~ Table 22-2.

Coarse Aggregates. Coarse Aggregates shall meet Colorado Department of Transportation Section 703.02 requirements and gradation as shown in **Table 22-3**.

~~4.~~ Table 22-3

~~5.~~ Table 22-3

~~6-3.~~ Fly Ash. Fly ash shall comply with **Colorado Department of Transportation Section 701.02**.

~~7-4.~~ Water. Water shall meet the requirements of **Colorado Department of Transportation Section 712.01**.

~~8-5.~~ Air Entraining and Chemical Admixtures. Shall meet the requirements of **Colorado Department of Transportation Sections 711.02 and 711.03**. No additive manufactured with the purposeful addition of chloride shall be permitted. Water-reducing admixtures are used when concrete temperatures are as follows: Type A is used with ambient temperature range of 50 to 90 degrees inclusive; Type D is used when ambient temperature is over 90 degrees.

Formatted: Heading 5, Space Before: 2 pt, After: 3 pt

Formatted: Font: Bold

Formatted: Font: 12 pt, Bold, Do not check spelling or grammar

Formatted: Font: Bold, Do not check spelling or grammar

Formatted: Heading 5, Indent: Hanging: 0.25", Space Before: 2 pt, After: 3 pt, Don't keep with next

Formatted: Font: Bold

Formatted: Font: 12 pt, Bold

Formatted: Font: Bold, Do not check spelling or grammar

Formatted: Indent: Left: 0.75", Hanging: 0.25", No bullets or numbering

**Table 22-2
 Fine Aggregates for Portland Cement Concrete**

Sieve Size or Test Procedure	Percent Passing or Test Requirement
Friable Particles, %	1.0, Maximum
Coal & Lignite, %	1.0, Maximum
Deleterious Material (AASHTO T-1 1), %	3, Maximum
Sand Equivalent (AASHTO T 176), %	80, Minimum
Fineness Modulus	2.50–3.50
Sodium Sulfate Soundness, %	20.0, Maximum

**Table 22-3
 Coarse Aggregates for Portland Cement Concrete**

Sieve Size or Test Procedure	Percent Passing or Test Requirement
2"	100
1-1/2"	95–100
3/4"	35–70
3/8"	10–30
#4	0–5
#200	1.0, Max. (1.5% if crusher fines)
% Wear	45, Maximum
Clay Lumps and Friable Particles, %	2.0, Maximum
Coal and Lignite, %	0.5, Maximum
Sodium Sulfate Soundness, %	12, Maximum

B. Concrete Forms

Refer to **Section 22.3.7 A.4.I**. Removal of forms shall occur at no less than 12 hours.

C. Construction

1. **Placing.** Concrete pavement may be placed using slipform methods or fixed forms. The concrete shall be deposited on moist subgrade in such a manner as to require as little rehandling as possible. Reasonable care shall be taken to prevent any segregation of the concrete materials. Workers shall not be allowed to walk in freshly mixed concrete with boots or shoes coated with earth or foreign substances.
2. **Vibrating.** Concrete shall be thoroughly consolidated against and along the faces of all forms and along the full length and on both sides of all joint assemblies by means of vibrators inserted in the concrete. Vibrators shall not be permitted to come in contact with a joint assembly, the grade, or a side form. Vibrators shall not be used to move the concrete into place.

3. Consolidation and Floating. The concrete shall be struck off and consolidated with a mechanical finishing machine, vibrating screed, or hand finishing methods. A slipform paver may also be used. After the concrete has been struck off and consolidated and joints formed (if necessary), it shall be leveled with a bull float having a handle to permit operation from the edge of the pavement. Any excess water and laitances shall be removed from the surface of the pavement. The straightedge shall be operated at 90 degrees to the transverse joints and shall be overlapped 1/2 of its length after each pass. Irregularities shall be corrected by adding or removing concrete. All disturbed places shall again be straight-edged. The use of hand tools shall be kept to a minimum. They may be used in areas not accessible to finishing equipment and for compacting concrete in the vicinity of formed joints.
4. Joints. Transverse and longitudinal joints shall be constructed to the dimensions and at the spacing shown on the plans. Transverse joints shall extend the entire width of the pavement and through the curbs. Joints may be formed in the plastic concrete or sawed after the concrete has hardened. Tooled joints may be constructed by depressing an approved tool into the plastic concrete cut a minimum of 1/3 the thickness of the slab.

Sawing of joints shall begin as soon as the concrete has hardened sufficiently to permit sawing without excessive raveling and before uncontrolled cracking occurs. If necessary, the sawing operations shall be carried on both day and night, regardless of weather conditions. At Contractor's option, tooled joints may be installed during initial placement to control cracking.

- a. Construction Joints. All longitudinal joints may be construction joints at the Contractor's option. Transverse construction joints shall be installed whenever the placing of concrete is suspended an excessive length of time as determined by the Local Entity Engineer.
 - b. Joint Filling. Joints shall be filled in accordance with CDOT 412.18 before the pavement is opened to traffic. Prior to filling, all foreign material shall be removed from the joints and the joints shall be thoroughly dry. Where preformed compression-type sealers are used, they shall be lubricated to allow the sealer to be inserted the full depth of the joint. Liquid elastic type fillers shall be poured to within 1/4 inch of the top of the joint. Care should be taken to keep from over-filling the joint.
5. Curing. Refer to the Materials Specification in CDOT 601.13 for concrete curing methods.
 6. Opening to Traffic. The Local Entity Engineer shall decide when the pavement shall be opened to traffic. It shall not be opened to traffic until the field-cured concrete has attained a flexural strength of 450 psi, and a compressive strength of 3,000 psi or .80 F_c' , whichever is greater. If such tests are not conducted, the pavement shall not be opened to traffic until 14 days after the concrete is placed. Before opening to traffic, the pavement shall be cleaned.

D. Warranty

Refer to **Section 22.4.3 H** and substitute the word “street” for the words “curb, gutters, walks, driveways and crosspans.”

E. Initial and Final Acceptance

Refer to **Section 22.4.3 I**.

~~22.5.7~~ **22.5.6 Asphalt Hot Bituminous Pavement – Superpave Method**

This section specifies materials and methods to be used for constructing superior performing pavements (~~Superpave~~) for streets, or other miscellaneous areas within the Right-of-Way. This work shall consist of constructing one or more courses of plant mix hot ~~bituminous asphalt~~ pavement, overlay, or leveling course on a prepared foundation and to the finished dimensions shown on the plans, or as directed by the Local Entity Engineer. (**Reference CDOT 403**)

A. Materials

1. Aggregates – All Aggregates shall conform to the current Colorado Department of Transportation “Standard Specifications for Road and Bridge Construction”

~~a. Aggregate for Hot Plant Mix Bituminous Pavement. Aggregates shall be crushed stone, crushed slag, crushed gravel, or natural gravel which conform to the requirements of AASHTO M147, as hereinafter supplemented. Aggregate for hot plant mix bituminous pavement shall be in accordance with CDOT Specifications Section 703.04, as shown in Table 22-4 below.~~

**Table 22-4
(CDOT 703-3)
Master Range Table for Hot Bituminous Pavement**

Sieve Size	Mass-Percent Passing Square-Mesh Sieves		
	Grading S	Grading SG	Grading SX
37.5 mm (1-1/2")		100	
25.0 mm (1")	100	90-100	
19.0 mm (3/4")	90-100		100
12.5 mm (1/2")	*	*	90-100
9.5 mm (3/8")	*	*	*
4.75 mm (#4)	*	*	*
2.36 mm (#8)	23-49	19-45	28-58
1.18 mm (#16)			
600 µm (#30)	*	*	*
300 µm (#50)			
150 µm (#100)			
75 µm (#200)	2-8	1-7	2-10

*These additional CDOT Form 43 Screens will initially be established for the

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.5 Pavement

~~Contractor's Quality Control Testing using values from the As Used Gradation shown on the Design Mix.~~

- ~~b. **New Aggregate.** Only aggregate from Local Entity pre-qualified sources shall be used. The mineral aggregate shall consist of hard, durable particles, or fragments of stone or crushed gravel having incorporated in it limestone dust, Portland cement, or other acceptable binder material, in such proportions that the whole will be a homogenous material after mixing at the asphalt plant. The mineral aggregate shall be clean and free from disintegrated stone, vegetable matter, clay lumps, or other deleterious substances. Aggregate may be conditionally accepted in stockpile at the plant site.~~
- ~~c. **Coarse Aggregate Angularity.** Coarse aggregate angularity is defined as the percent by weight of the aggregate particles larger than the #4 sieve having two or more fractured faces.~~
- ~~d. **Fine Aggregate Angularity.** Fine aggregate angularity is defined as a minimum of 45 percent air voids present on loosely compacted aggregate that passes the #8 sieve. Fine aggregate angularity is measured on the fine aggregate portion of the blended aggregate by **AASHTO Standard Method of Test TP 33** (ASTM Standard Method of Test C1252).~~
- ~~e. **Clay Content.** Clay content is a measure of the amount of clay material present in the portion of aggregate that passes the #4 sieve. Clay content is measured on the portion of the blended aggregate passing the #4 sieve by means of the sand equivalent test (**AASHTO Standard Method of Test T176**). Clay content criteria for increasing levels of total traffic in ESALS are presented in **Table 22-5**.~~

**Table 22-5
Clay Content Criteria**

Traffic (ESALS)	Sand Equivalent
$<3 \times 10^5$	40
$<3 \times 10^7$	45
$\geq 3 \times 10^7$	50

- ~~f. **Thin, Elongated Particles.** Thin, elongated particles are the coarse aggregate particles that have a ratio of maximum to minimum dimensions greater than 5. The percentage of thin, elongated particles is measured on the portion of the blended aggregate retained on the #4 sieve by ASTM Standard Method of Test D 4791. Maximum criteria for thin, elongated particles for increasing levels of traffic in ESALS are presented in **Table 22-6**.~~

**Table 22-6
Criteria for Thin, Elongated Particles**

Traffic (ESALS)	Maximum Weight Percent of Thin, Elongated Particles
$\geq 4 \times 10^6$	10

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.5 Pavement

~~g. Dust Proportion. Dust proportion is defined as the ratio of the percent by weight of aggregate passing the #200 sieve to the effective asphalt binder, content expressed as percent by weight of the total mix. Dust proportion for all bitumen contents shall be presented in the mix design for information only.~~

~~h. Asphalt Mix Design~~

~~1) Test Methods and Criteria. The design mix for hot bituminous pavement shall conform to~~

~~2)–~~

~~3) Table 22-7 and Table 22-8.~~

DRAFT

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.5 Pavement

Table 22-4
Design Mix Criteria

Property	Test Method	Value for All Gradings (gyrations)		Reference
		(75)	(100)	
Air Voids, percent at: N (design)	CPL 5115	3.5 – 4.5	3.5 – 4.5	
Lab Compaction (gyrations): N (design)	CPL 5115	75	100	
Hveem Stability, minimum	CPL 5106	28	30	
Aggregate Retained on the 4.75mm (No. 4) sieve with at least 2 mechanically induced fractured faces, % minimum	CP 45	90	90	
Accelerated Moisture Susceptibility Tensile Strength Ratio (Lottman), minimum	CPL 5109: Method B	80	80	
Minimum Dry Split Tensile Strength, psi	CPL 5109: Method B	30	30	
Grade of Asphalt Binder, Top Layer	-	See Table 22-7		
Grade of Asphalt Binder, below Top Layer	-	See Table 22-7		
Voids in Mineral Aggregate (VMA), % minimum	CP 48	See Table 22-6		
Voids Filled with Asphalt (VFA), %	AI SP-2	65 - 80	65 - 75	
Aggregate Design Grading	CDOT	S or SX	S or SX	
Laboratory Design Temperatures	-	See Table 22-5		
Note:				
1. AI SP-2 = Asphalt Institute Superpave Series No. 2				
2. The current version of CP (Colorado Department of Transportation) standards is available from the Region 4 Materials Engineer.				
3. Warm mix asphalt is allowed as an alternate to Hot Mix Asphalt, provided all material requirements and specifications are met and approved by the Local Entity Engineer. The supplier and method of warm mix asphalt must be on CDOT approve list.				
4. Gyration design revolution (Ndes) will be 75 unless otherwise specified by the Local Entity Engineer based upon project specific criteria and/or traffic levels.				

Table 22-7
Design Mix Criteria

Property	Test Method	Value for All Gradings (gyrations)		Reference
		(75)	(100)	
Air Voids, percent at: N _{initial} (for information only)	CPL-5115	>9.5	>14	Refer to Table "22-15"
N _{design}		3.5-4.5	3.5-4.5	
Lab Compaction (gyrations): N _{initial} (for information only)	CPL-5115	7	8	Refer to Table "22-15"

Formatted: Highlight

Formatted: Highlight

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.5 Pavement

Property	Test Method	Value for All Gradings (gyrations)		Reference
		(75)	(100)	
N _{design}		75	100	
Hveem Stability, minimum	CPL-5106	28	30	
Aggregate Retained on the 4.75mm (No. 4) sieve with at least 2 mechanically induced fractured faces, % minimum	CP-45	90 (80 for SG)	90 (80 for SG)	
Accelerated Moisture Susceptibility Tensile Strength Ratio (Lottman), minimum	CPL-5109; Method B	80	80	
Minimum Dry Split Tensile Strength, kPa (psi)	CPL-5109; Method B	205 (30)	205 (30)	
Grade of Asphalt Cement, Top Layer				Refer to Table "22-15 thru 22-17"
Grade of Asphalt Cement, below Top Layer				Refer to Table "22-14"
Voids in Mineral Aggregate (VMA), % minimum	CP-48			Refer to Table "22-13"
Voids Filled with Asphalt (VFA), %	AI SP-2	65-80	65-75	
Design Grading				Refer to Table "22-8"
Laboratory Design Temperatures				Refer to Table "23-5"
Note:				
1. AI SP-2 = Asphalt Institute Superpave Series No. 2				
2. The current version of CP (Colorado Department of Transportation) standards is available from the Region 4 Materials Engineer				
3. Mixes with gradations having less than 40% passing the 4.75 mm (No. 4) sieve shall be approached with caution because of constructability problems.				
4. Table I of CPL-5115 contains the laboratory mixing and compaction temperatures to be used for mix design development and laboratory verification of project produced mixtures.				

Tom and Mike are working on the revised table

Formatted: Font: 14 pt, Font color: Red

Table 22-458
Laboratory Mix Design Temperatures

Superpave Binder Grade	Laboratory Mixing Temperature, °C (°F)	Laboratory Compaction Temperature, °C (°F)
PG 58 - 22	154 (310)	138 (280)
PG 58 - 28	154 (310)	138 (280)
PG 58 - 34	154 (310)	138 (280)
PG 64 - 22	163 (325)	149 (300)
PG 64 - 28	163 (325)	149 (300)
PG 70 - 28	163 (325)	149 (300)
PG 76 - 28	163 (325)	149 (300)

~~Warm Mix Asphalt is exempt from this table~~
*All temperatures in this table have a tolerance of ± 2.8°C (± 5°F)

Table 22-569
Minimum Voids in the Mineral Aggregate (VMA)

Nominal Maximum Size ¹ , mm (inches)	Design Air Voids ²		
	3.5%	4.0%	4.5%
37.5 (1-1/2)	11.5	12.0	12.5
25.0 (1)	12.5	13.0	13.5
19.0 (3/4)	13.5	14.0	14.5
12.5 (1/2)	14.5	15.0	15.5
9.5 (3/8)	15.5	16.0	16.5

Notes:
1. The Nominal Maximum Size is defined as one sieve larger than the first sieve to retain more than 10%.
2. Interpolate specified VMA values for design air voids between those listed.
3. Air Void Criteria: A design air void range of 3.5 to 4.5% with a target of 4.0% will be used on all mixes. The air void criteria will be applied to the approval of the design mix.

4)1) ~~Selection of SuperPave Gyratory Design Revolutions.~~ Superpave Gyratory Design Revolutions shall be as follows: for arterial roadways 100 gyrations; for collector and local roadways 75 gyrations.

2. Selection of Performance Graded Binders (Asphalt Cement) for SuperPave Mix Design

a. Asphalt ~~Binders~~Cements Permitted

The ~~SuperPave System specifies~~ Asphalt ~~binders cement~~ properties to address pavement performance for the climate and traffic found in the specific area of the project. The high and low temperature properties required are then specified according to a percent reliability against rutting (high temperature properties) and thermal cracking (low temperature properties) found for a given pavement. The high and low temperatures used to select asphalt cement

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.5 Pavement

grades are pavement temperatures at 20 mm below the pavement surface and at the pavement surface respectively.

The physical properties that the asphalt cement are required to meet stay the same. What changes is the temperature at which these asphalt cement properties must be met.

Because of the many climate conditions, specifying asphalt cements based on climate conditions results in a very large number of asphalt cements nationwide. However, only a limited number of PG grades are needed for Colorado. Therefore, only ~~threeseven (7)~~ PG Graded Binders will generally be permitted in these specifications. ~~PG 58-28, PG 64-22, Pg 64-28~~ They are as given in ~~Table 22-10~~:

**Table 22-10
Asphalt Cements Permitted**

Polymer Modified	Unmodified
PG 76-28	PG 64-22
PG 70-28	
PG 64-28	PG 58-28
PG 58-34	PG 58-34

~~SuperPave Graded Asphalt~~ Binders shall conform to the requirements listed in ~~the current Colorado Department of Transportation Table 702-2 of the 1999 CDOT Standard Specifications for Road and Bridge Construction or current revision.~~

b. Binder Grades

In an effort to simplify the binder selection process, the following binder grades have been specified for the various types of construction and road classifications. Refer to ~~Table 22-6~~ ~~Table 22-6~~ ~~Table 22-11~~

**Table 22-6614
Binder Grade Requirement**

New Construction – Top Lift or Reconstruction		Lower Lift, Overlay	
Local/Residential	PG 58-28	Local/Residential	PG 58-28
Minor Collector	PG 58-28	Minor Collector	PG 58-28
Major Collector	PG 64-28	Major Collector	PG 64-28
Industrial/Commercial	PG 64-28	Industrial/Commercial	PG 64-22
Arterial	PG 64-28	Arterial	PG 64-22

Need more Discussion

The above Binder grades are as outlined in the following two subsections below:

- Formatted: Font: Bold
- Formatted: Font: Bold, Not Highlight
- Formatted: Font: Bold, Do not check spelling or grammar
- Formatted: Font: Bold, Not Highlight
- Formatted: Font: Bold
- Formatted: Font: Bold, Not Highlight
- Formatted: Font: Bold, Do not check spelling or grammar
- Formatted: Font: Bold, Not Highlight
- Formatted: Font: 14 pt, Font color: Red

e. Grade Bumping

Grade bumping means selecting an asphalt cement grade that is one or more high temperature grades higher than the minimums required in **Table 22-12**, to account for extreme traffic flow and traffic loading conditions.

The local entities may require grade bumping on Industrial/Commercial, Major Collector and Arterial roadways. Grade bumping will not be required on Local/Residential or Minor Collector roadways.

**Table 22-12
Grade Bumping Criteria**

Condition	Recommendation
Slow Moving Traffic Loads	-1 Grade Higher Than Free Flowing
Standing Traffic Loads	-2 Grade Higher Than Free Flowing
Total 18k ESAL \geq 10,000,000	-1 Grade Higher Than Free Flowing
Total 18k ESAL \geq 30,000,000	-2 Grade Higher Than Free Flowing
1. Free flowing traffic is traffic at speeds greater than 45 miles/hour 2. Slow moving traffic is traffic moving between 12 miles/hour and 45 miles/hour 3. Standing traffic is traffic moving less than 12mph 4. No adjustment will be allowed for the low temperature grade because of traffic speed or volume.	

d. Asphalt Cement Selection For Lower Lifts

Local entities may allow a lower grade of asphalt cement to be utilized in the lower layers of a pavement section in accordance with **Table 22-13**:

For pavements with multiple layers, a lesser grade of asphalt cement may be specified for the lower layers based on the amount of the material needed and other economical design decisions. In many cases, the requirements for the lower layers might be obtained with an unmodified or more economical grade of asphalt cement. At least 10,000 tons of HMA in the lower lifts is needed before a separate asphalt cement is specified for the lower lift.

**Table 22-13
Grade Reduction for Lower Lifts**

Lift	High Temperature Grade Specified for the Project (Assumes Mix in the Top Lift)			
Top	58	64	70	76
4" or more below the surface	52	58	64	70
6-inch or more below the surface	52	52	58	64

- 3. Anti-Stripping Additive.** An anti-stripping additive shall be required and the following shall apply:

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.5 Pavement

~~a. Hydrated Lime. If additive is not added at refinery, a minimum of one percent hydrated lime by mass (weight) of the combined aggregate shall be added to the aggregate for all hot bituminous asphalt pavement. Hydrated lime shall meet the requirements of ASTM C207, Type N. The “F” factor used in calculating P values for lime gradation shall be 0.3.~~

~~a. Liquid Additive~~

- ~~1) The Developer shall use an approved anti-stripping additive. The amount of additive used shall be a minimum of 0.5 percent by mass (weight) of the asphalt cement.~~
- ~~2) In-Line Blender. The additive shall be added at the refinery or at the hot plant. If liquid anti-stripping additive is added at the plant, an approved in-line blender must be used. The blender shall be in the line from the storage tank to the drier drum or pugmill. The blender shall apply sufficient mixing action to thoroughly mix the asphalt cement and anti-stripping additive.~~

~~b. Liquid Additive~~

- ~~1) The Developer shall use an approved anti-stripping additive. The amount of additive used shall be a minimum of 0.5 percent by mass (weight) of the asphalt cement.~~
- ~~2) In-Line Blender. The additive shall be added at the refinery or at the hot plant. If liquid anti-stripping additive is added at the plant, an approved in-line blender must be used. The blender shall be in the line from the storage tank to the drier drum or pugmill. The blender shall apply sufficient mixing action to thoroughly mix the asphalt cement and anti-stripping additive.~~

~~b. Hydrated Lime. If additive is not added at refinery, a minimum of one percent hydrated lime by mass (weight) of the combined aggregate shall be added to the aggregate for all hot bituminous pavement. Hydrated lime shall meet the requirements of ASTM C207, Type N. The “F” factor used in calculating P values for lime gradation shall be 0.3.~~

4. Filler. Filler shall meet the requirements of AASHTO M17.

B. Superpave Job Mix

1. Testing Laboratory. See Chapter 23, Job Mix for **Bituminous Asphalt Asphaltic Concrete Pavement**.
2. Composition of Mixtures. The **Bituminous Asphalt** plant mix shall be composed of a mixture of aggregate, filler or additives if required and approved, **bituminous asphalt** material, and reclaimed material if permitted and used.
3. Mix Design. The Contractor shall submit the following to the Engineer for each proposed mix design:

Formatted: Font: Arial-BoldMT, 12.5 pt, No underline

Formatted: Indent: Left: 1", No bullets or numbering

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.5 Pavement

- a. A proposed job-mix gradation for each mixture certified by A proposed mix design job-mix gradation for each mixture certified by an AASHTO accredited laboratory complying with CDOT Field Materials Manual Colorado Procedure 10 the independent laboratory or CDOT Field Materials Manual a AASHTO Materials Reference Laboratory (AMRL) Certified laboratory. "ARML Recognized" shall be wholly within the Master Range Table, **Table 22-7** before the tolerances shown in **Table 22-16** are applied. The mass of lime shall be included in the total mass of the material passing the No. 200 sieve. The restricted zone boundaries given in the Asphalt Institute's **Superpave Series No. 2 (SP-2) Manual**, Appendix B, are to be used as guidelines in mix design development. However, the job-mix gradation is not required to pass above or below the restricted zone boundaries.
- b. The aggregate source, percentage of each element used in producing the final mix, the gradation of each element, and the proposed job-mix formula (JMF) gradation. The gradation used shall be based on the Contractor's JMF.
- c. The name of the asphalt cement supplier.
4. Sampling for JMF Testing. The contractor's proposed job-mix formula for each hot bituminous asphalt pavement grading will be tested utilizing materials actual produced and stockpiled.
 5. JMF Target Values. The job-mix formula for each mixture shall establish a single percentage of aggregate passing each required sieve size, a single percentage of bituminous asphalt material to be added to the aggregate, and a single temperature for the mixture at the discharge point of the plant.
 6. Aggregate Source Changes. Should a change in the sources of material be made, a new job-mix formula shall be established and approved in accordance with section 3 before the new material is used.
 7. Recycle Asphalt Pavement. The hot bituminous asphalt pavement shall not contain more than 2015 percent reclaimed asphalt pavement where allowed. The reclaimed asphalt pavement shall meet the requirements of CDOT subsection 703.04. Reclaimed asphalt pavement shall not be used in the top 2" (wearing course) of any pavement section.
 8. Aggregate Quality. Test for cleanliness, abrasion loss, and percent of fractured faces will be made on representative samples of aggregate taken during production or from the stockpiles.
 9. JMF Compliance. When laboratory tests indicate that a proposed job-mix formula complies with the specifications the JMF may be submitted for mix design approval in accordance with section 3. Mix Design Approval.
 10. Mix Design Approval. Mix designs will be approved on a Laboratory/Production approval system. Initial approval will be given based on laboratory design. Production approval will then be given based on testing conducted on plant mixed samples to verify the approved laboratory design.
New mix design shall be submitted for approval for a two each calendar year and shall remain in effect for a period with a one point verification submitted and

Formatted: Font: Times New Roman

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.5 Pavement

~~approved on an annual basis not extending beyond the end of that calendar year.~~
Should a change in sources of materials be made a new mix design will be required & shall remain in effect for the remainder of the ~~at approval period~~ calendar year.

- a. Laboratory Mix Design Approval. The Developer may receive preliminary mix design approval of a new ~~HBP asphalt~~ mix design, based on the following procedure:
- 1) The mix designs will be performed by ~~an AASHTO accredited laboratory complying with CDOT Field Materials Manual Colorado Procedure 10 AASHTO Materials Reference Laboratory (AMRL) Certified laboratory an independent laboratory or CDOT Field Materials Manual “ARML Recognized”~~ and approved by the Local Entity.
 - 2) Conditions. The following conditions shall apply to this preliminary approval:
 - a) Written Request and Submittals. The Developer shall make a written request for preliminary mix design approval, and submit three copies of the independent lab mix design containing all the information required in Laboratory Mix Design checklist in Appendix E-7.
 - b) Test Results. The results of all required tests shall meet the mix design specification requirements listed in Table 23.5.
 - c) Asphalt Content. The Local Entity Engineer, only, shall approve the asphalt content based on the private lab mix design.
- b. Production Mix Design Approval. The Developer may receive and maintain production mix design approval of an HMA mix design, based on the following procedure:
- 1) Following laboratory mix design approval verification of mix properties will be performed by an independent laboratory on plant-produced mix and approved by the Local Entity. This verification is to be performed on or before the first day of production within the GMA.
 - 2) To maintain production mix design approval verification of mix properties shall be performed by an independent laboratory on plant-produced mix and approved by the Local Entity every 10,000 ton of mix produced.
 - 3) Conditions. The following conditions shall apply to production mix design approval:
 - a) Written Request and Submittals. The Developer shall make a written request for production mix design approval, and submit the results of the mix verification report performed by a independent lab.
 - b) Test Results. The results of all required tests shall meet the mix design specification within the tolerances listed in ~~Table 22-7~~ Table 22-14.

Formatted: Font: Bold

Formatted: Font: Bold

Table 22-7714
Tolerances for Hot Mix Asphalt

Element	Tolerance
Asphalt cement content	+/-0.30%
Voids in Mineral Aggregate (VMA)	+/-1.2%
Air Voids (Va)	+/-1.2%
Lottman	Min. 80
Hot Mix Asphalt Gradation	
Passing the 3/8" and larger sieves	+/-6%
Passing the No. 4 and No. 8 sieves	+/-5%
Passing the No. 30 sieve	+/-4%
Passing the No. 200 sieve	+/-2%

- c) Local entity shall have 5 days to review production mix design verification test results and approve or reject the mix design.
- d) Stop Work. If the results of mix design verifications are not within the tolerances as determined by the local entity the contractor shall immediately stop paving within the GMA and submit a mitigation plan to the local agency for approval. If given approval paving may resume and a new mix design verification test will be performed on the first day of production. If after implementation of the mitigation plan the contractor is not capable of meeting the original mix design specifications he shall complete and submit a new mix design to the local entity for laboratory mix design approval.

22.5.8-22.5.7 Construction Requirements

- 1. Weather.
 - a. Placement Temperatures. Plant mix pavement shall be placed only on properly prepared unfrozen surfaces which are free of water, snow, and ice. The plant mix pavement shall be placed only when both the air and surface temperatures equal or exceed the temperatures specified in ~~Table 22-8~~~~Table 22-8~~~~Table 22-15~~ and the Local Entity Engineer determines that the weather conditions permit the pavement to be properly placed and compacted.

Formatted: Font: Bold
Formatted: Font: Bold

Table 22-8815
Placement Temperature Limitations in °F

Compacted Layer Thickness in Mm (Inches)	Minimum Surface and Air Temperature ° F	
	Top Layer	Layers Below Top Layer
2" – 3"	50	40
3 or more	45	35

Note: Air temperature is taken in the shade. Surface is defined as the existing base on which the new pavement is to be placed. If the temperature falls below the minimum air or surface temperatures, paving shall stop.

- b. Temporary Pavement Layer. The Work shall be scheduled so that no planed or recycled surface is left without resurfacing for more than 10 calendar days from October 1 to March 1. The Developer shall immediately place a temporary hot bituminousasphalt pavement layer on any surface that has been planed or recycled and cannot be resurfaced in accordance with the above temperature requirements within 10 calendar days after being planed or recycled.
- 1) Thickness. The minimum thickness of the temporary hot bituminousasphalt pavement layer shall be 2 inches. The Developer shall perform the quality control required to assure adequate quality of the hot bituminousasphalt pavement used in the temporary layer.
 - 2) Markings. All applicable pavement markings shall be applied to the temporary layer surface.
 - 3) Maintenance. The Developer shall maintain the temporary layer for the entire period that it is open to traffic. Distress that affects the ride, safety, or serviceability of the temporary layer shall be immediately corrected to the satisfaction of the Local Entity Engineer.
 - 4) Removal. The temporary hot bituminousasphalt pavement layer shall be removed when work resumes.

22.6 MISCELLANEOUS

22.6.1 Rebuilt Miscellaneous Structures

A. General

This section addresses removing, relaying, resetting, or adjusting structures, fences, guard rail, signs, pipe, end sections, traffic signals, and related materials. All designated items shall be carefully removed and every precaution taken to avoid damage. Coordinate relocation of permanent traffic devices with the Local Entity Engineer. The Developer will be required to replace or repair any material damaged due to their operations at their own expense. The work shall include the back-filling of any resulting trenches, holes, or pits.

B. Construction

1. Pipe to be re-laid and structures to be re-set shall be thoroughly cleaned. Removal sites shall be neatly backfilled with suitable material and compacted in accordance with these Standards.
2. All material that is unserviceable shall be handled according to **CDOT Specifications Section 210.02**.
3. Fences and gates should be rebuilt or reset according to **CDOT Specifications Section 210.04**.
4. Mailboxes complete with supporting structures are to be removed and reset according to **CDOT Specification Section 210.06**. Reset height shall be 42 to 48

inches. The box face shall be no closer than 2 feet from the curb face or edge of sidewalk, whichever is applicable.

5. Re-setting of all traffic control signs and traffic signaling devices will conform to **Section 22.6.2** and be coordinated with the Local Entity Engineer.
6. Structures shall be adjusted according to **CDOT Specifications Section 210.10**.
7. At no time shall manholes and valve boxes be covered up or buried. Valve boxes and manholes are to be maintained fully accessible at all times for emergency and maintenance operation by the Local Entity personnel.

22.6.2 Traffic Signals, Signing, and Striping

A. General

This section addresses the material specifications for traffic control devices as well as requirements for their installation.

The specification and installation of all traffic control devices shall conform to the **Manual on Uniform Traffic Control Devices** and the **Colorado Standard Specifications for Road and Bridge Construction**, latest edition.

Permanent signing, striping, and traffic signals, shall be in place before new roadways are completely opened to the public.

1. Traffic Control Devices on Public Property. The Developer shall submit a striping and signage plan approved by the Local Entity Engineer. The Developer shall install all traffic control devices, except signals. Devices shall be placed to conform to the drawing details.
2. Traffic Control Devices on Private Property.
 - a. Responsibility. All traffic control devices on private property; i.e., pavement markings, regulatory signs, fire lane signs, and handicapped parking signs shall be installed and maintained by the property owner.
 - b. Placement. A signage and striping plan specifying the various types and combinations of traffic control devices shall be submitted to the Local Entity Engineer for approval. Refer to **Chapter 3, Information Requirements for Construction Plans**, for requirements.

B. Traffic Signal

1. Signals. All permanently fixed traffic signals will typically be installed by the Local Entity.
2. Loop. For traffic loop installation, contact the Local Entity Engineer.

C. Traffic Signal Controller

All traffic signal controllers will typically be installed by the Local Entity.

D. Traffic Signing

1. Street Name Signs.

a. Materials. Street name signs shall be fabricated from Scotchlite reflective sheeting, Engineer grade, on 0.80 gauge aluminum or approved equal.

b. Installation.

1) Location. Street name signs shall be placed on diagonally opposite corners at each intersection at the point of curvature of the corner radius. Thus, they will be on the far right-hand side of the intersection for traffic on the major street. Tee intersections will also require two sign locations. Signs naming both streets shall be erected at each location. This requirement includes local and collector streets in residentially zoned areas.

2) Placement/Setback. The street name assembly is usually combined on top of stop signs. Sign placement for the stop sign or other regulatory sign shall govern in these cases. In other instances, the street name assembly should be placed according to the following, as measured from the edge of the sign:

a) Curb, Gutter and Sidewalk Combination. Two feet behind sidewalk.

(1) Curb with no Sidewalk or Detached Sidewalk. Two to three feet behind curb on local streets. On Collector streets, 4 to 5 feet behind curb, and on Arterial streets, 6 to 8 feet behind curb.

(2) No Curb or Gutter. Six to twelve feet from edge of pavement.

3) Mounting. Street name signs shall be mounted with two standard rivets (TL3806 EG, Drive Rivet) with nylon washers placed against the face. Typical installation includes four street name signs, two for each direction.

4) Post and Mounting Installation. Refer to Sections 22.6.2 D.6.a and 6.b.

2. Traffic Control Signs. Traffic control signs are categorized as regulatory, warning, and guide signs.

a. Materials. All regulatory signs shall be fabricated using reflective high intensity (or greater) grade sheeting, on aluminum blanks.

b. Installation. These signs shall be placed generally as per the MUTCD and the Colorado Supplement.

c. Mounting. Traffic control signs shall be mounted on existing sign posts, street lights, and utility poles where possible. Refer to **Section 22.6.2 D.6**.

3. Crosswalk Signs.

a. Materials, Installation, and Mounting. Materials for and installation and mounting of signs for crosswalks shall be in accordance with the above **Section 22.6.2 D.2**. All pedestrian crossing and W16-7P signs shall use fluorescent yellow/green (diamond grade) sheeting.

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.6 Miscellaneous

- b. Placement. A crosswalk sign shall be erected at the crosswalk or at minimum distance before the crosswalk. As per M.U.T.C.D. requirements, signs shall use Advanced Crossing “Ahead” placard, W16-9p, 24” x 10”.
4. Roundabout Signs.
- a. Materials, Installation and Mounting. Materials for and installation and mounting of signs for Roundabouts shall be in accordance with the above **Section 22.6.2 D.2**.
- b. Placement. The in advance warning and regulatory signs (refer to **Chapter 14, Traffic Control Devices**) and “Yield” sign shall be placed in accordance with MUTCD. The “Arrow” signs shall be placed two feet outside the edge of the circulating roadway per MUTCD between each entrance and exit of the roundabout. Refer to **Figure 8-14** for general locations.
5. Bikeway Signs. “No Parking” signs (R7-9a) as shown in **Construction Drawing 1402** shall be installed, generally, at intervals of 250 feet, at an angle of 45 degrees to the roadway.
6. Posts and Mountings.
- a. Materials. The sign post system shall be comprised of three sections, an anchor, post, and sign. The anchor specification shall be Telspar 22F12A- 03PG-2-1/4 inch square x 3 feet, 12 gauge, Anchor Stub with holes. The post specification shall be Telspar 20F12P-10PG – 2 inch square x 10 feet, 12 gauge, post with holes. Refer to **Section 22.6.2 D.2** for sign materials.
- b. Installation. The anchor is driven into the ground 30 to 33 inches with 6 to 3 inches above the adjacent ground level. The square post section with holes is inserted into the anchor six to eight inches and bolted with two 2-1/2 inch long, 3/8 inch hex head bolts. These bolts are installed at the top two holes at 90 degrees to one another.
- c. Mounting. The top of the sign shall be mounted with one TL3806 EG Drive Rivet with a nylon washer on the sign face. The bottom of the sign shall be mounted using one 5/16” hex bolt, one metal washer, and one nylon washer against the sign face. A 5/16” hex nut is used to secure the bolt on the backside of the post.
7. Sign Height. Signs shall be mounted at a height of 7 feet, measured from the bottom of the sign to the top of curb. The height to the bottom of a secondary sign mounted below another sign shall be 6 feet from the top of the curb. Where a traffic control sign is mounted on the same post with a street name sign, it shall be placed below the street name sign, with the bottom of the traffic control sign 7 feet from the top of curb.

E. Traffic Striping and Marking

1. General. Existing and temporary pavement striping and marking shall be removed prior to new installations according **CDOT Specifications Section 202.05**.

Surfaces shall be thoroughly cleaned and prepared prior to application of striping and marking.

Chapter 22 – MATERIALS AND CONSTRUCTION SPECIFICATIONS
Section 22.6 Miscellaneous

A Right-of-Way Work Permit is required prior to striping removals and installations. Refer to **Chapter 6, Permits**, for permits.

2. Striping.

a. Striping Materials.

- 1) Asphalt Pavement. All new striping on asphalt streets shall meet the minimum standards for latex applications. A minimum of 15 mils thick (when dry) of latex paint (Flint Trading Co.) specified in **CDOT Specifications Section 708.05** will be used. The paint will be used with standard moisture resistant beads specified in **CDOT Specifications Section 713.08** and designed for waterborne paint. The beads shall be applied at a minimum rate of 6.5 pounds per gallon of paint applied.
- 2) Concrete Pavement. Striping on concrete streets shall meet the minimum standards for epoxy applications as specified in **CDOT Specifications Section 713.17**.

b. Pre-Striping Materials. Layout (spot taping) of striping shall be done using standard, reflective 3M Temporary (foil backed) roadway marking tape specified according to **CDOT Specifications Sections 713.14 and 713.15** or tabs (for chip seals or slurry seals only). Tape shall be 4 x 4 inches. Tabs and tape shall be the same color as the future striping and symbols.

c. Pre-striping. Prior to permanent installation of traffic striping, the contractor shall place temporary tabs or tape depicting alignment and placement of the same. Prior to the use of tape or tabs, a layout shall be done neatly using string or chalk line, inspected, and adjusted as necessary.

d. Layout and Tab Installation. Installation of temporary marking tape shall be according to **CDOT Specifications Section 627.08**. There shall be a tab or tape for each line. Therefore, in the case of a double line, there will be two tabs, one for each line. To improve night visibility, protective tab covers shall be removed immediately after chip, slurry, or sand sealing.

A typical 50-foot spacing of tabs or temporary tape for each spot will be used. A 25-foot spacing of tab or tape will be used within 75 feet of a public street intersection or marked crosswalk. Breaks in each line shall be marked with a "T" (using tape) to define the end and beginning of lines.

e. Striping Application. Application rates and specifications for striping shall be according to **CDOT Specifications Section 627.04**. Striping on new asphalt and/or concrete pavement must receive two (2) full applications (two coats) of paint with beads. Refer to **Construction Drawings 1403 and 1404**.

- 1) Centerline. All centerline striping shall be double yellow, each 4 inch wide, with a 4-inch minimum gap between the two.

- 2) Parking Stalls and Angle Parking. All striping for parking conditions shall be white and 4 inches wide. All edge lines of parking areas shall also be white and a minimum of 4 inches wide.
- 3) Turn Bays. If a turn bay occurs on a curve, it shall be marked with an 8-inch wide dotted extension line, in accordance with **MUTCD** requirements.

3. Marking.

- a. Materials. All pavement markings such as arrows, onlys, crosswalks, stopbars, and bike symbols shall meet minimum standards for preformed thermoplastic. Refer to **Chapter 14, Traffic Control Devices**, for specifications. A minimum thickness of 150 mil (Flint Trading Co.) or approved equal, shall be required. Markings on new concrete (and where required by manufacturer on asphalt) shall use correct primer as required by **CDOT Specifications Section 708.07**.
- b. Application. Application specifications shall be according to **CDOT Specifications Sections 627.06 and 627.07**.
- c. Stopbars. Stopbars are to be installed in accordance with the Local Entity Engineer. Refer to **Construction Drawing 1403**.
- d. Crosswalks. Crosswalks will be marked using the continental/Denver style starting from the flowline (or extended flowline) then back from the intersection the standard 9 feet in Loveland (GMA and city limits), or 12 feet in Fort Collins (GMA and city limits). Where a concrete pan is present, the specific manufacturer's primer must be applied as per manufacturer's specifications. Refer to **Construction Drawings 1403, 1404 and 1405**.
- e. Roundabouts.
 - 1) Yield Marking. The yield line shall be placed where the entry roadway meets the outer edge of the circulatory roadway (where the entering vehicles wait). Refer to **Figures 8-13 and 8-14**.
 - 2) Crosswalk. The crosswalk shall be placed approximately one car length in advance of each entry point. Refer to **Figure 8-13**.
- f. Bike Lanes. All on-street bike lanes shall be designated with bicycle arrow signs. See **Construction Drawings 1406 and 1408L**. The arrow designates the direction of recommended travel. The bike lane symbols shall be placed approximately 50 feet downstream from all intersections. Refer to **Construction Drawings 1403, 1404 and 1410**.

22.6.3 Bus Shelters

Shelters shall be placed on a 6-inch-thick concrete pad. The size and location of the pad as well as shelter criteria are discussed in **Chapter 16, Pedestrian Facilities**. The material and construction specifications are the same as those for concrete sidewalks. Refer to **Section 22.4**, concerning non-structural concrete.

22.6.4 Streetscape Standards - Fort Collins (City Limits Only)

See Appendix “C” – City of Fort Collins Streetscape Standards.

DRAFT